



Product Description

Chlorinated Rubber Top coat is an one component Chlorinated Rubber Top coat with good glass and color. retention durability in sever marine atmosphere and excellent water resistance.

Recommended Use

This coating (in the chlorinated rubber system) is used for protection exterior and interior steel structures in moderately to severely corrosive environment and water treatment plants for example ship hulls and bridges.

Surface Preparation

All surface to be coated clean, dry and free from contamination prior to paint application .all surfaces should be assessed and treated in accordance with ISO8504:1992.Oil or grease should be removed in accordance with SSPC-SP1 solvent cleaning.

Product Description

Shade :	RAL colors
Pigment & extender :	30%-32%
Volume solids:	38%-42%
Dry film thickness:	40μ
Wet film thickness:	90-100 μ
Theoretical spreading rate:	5-6 m ² /kg
Thinner:	Chlorinated Rubber Thinner
Shelf life:	12 months
Specific gravity :	1.15-1.25 Kg/Lit
Viscosity:	90-100 k
Salt spray chamber test:	200h
Humidistatic chamber test:	200 h
Touch dry time:	30 min

Temperature	Touch dry	Recoating
15 °C	3-5 hours	20 hours
25 °C	2-3 hours	14 hours
40 °C	1-2 hours	10 hours

Environmental Conditions

To prevent moisture condensation during application surface temperature must be at least 3 °C above the dew point .In hot climate, material temperature should be 20 to 25°C.For satisfactory cure air and surface temperature must be above 10°C.Never apply coatings under reverse environmental condition .Paint shall not be applied when wind speed is in excess of 7 m/s.

Application Details

Airless spray	Tip range: 0.017-0.019 inch Total out put pressure at spray tip not less than 141 bar.
Air spray	Nozzle orifice:1.8-2 mm Nozzle pressure:3-5 bar
Brush	20-25μ (touch up)
Roller	20-25μ (touch up)





**RANGIN ALVAN
ZEREH SEPAHAN**

MANUFACTURE OF INDUSTRIAL AND CONSTRUCTION PAINTS

■ **RZS-4131| Chlorinated Rubber Topcoat**

Application Procedure

- 1: Flush all equipment with recommended cleaner before use.
- 2: Stir the product thoroughly with a power mixer.
- 3: For air spray, thin with no more than 5-7% of recommend thinner for workability for airless -spray 5% of thinner is normally sufficient.
- 4: Apply wet coat by parallel passes overlap each pass 50% to avoid bare areas.
- 5: Double coat all welds, rough spots, sharp edges, rivets, bolts, etc. to ensure proper thickness.
- 6: If the minimum interval coating of this coating is exceeded, roughening of the surface is necessary to ensure inter coat adhesion.
- 7: Clean all equipment with recommend cleaner immediately after use.

Safety

This product is flammable keep away from heat and open flame operator (accordance MSDS of this product) must use special mask and safety gloves and operation should be performed in environments which is equipped with suitable air conditions.

Storage Conditions

Store in closed container and away from direct sunlight at temperature of 5-35 °C.

ADDRESS: ISFAHAN, NAJAFABAD 2 INDUSTRIAL TOWN, KARGAR SQUARE, RAZI ST., SUB-16, NO. 9

TEL: 09131250751 | 09133044014 **WEBSITE:** WWW.RANGINALVANZEREH.COM **EMAIL:** INFO@RANGINALVANZEREH.COM

