

CONTAINS: Water (7732-18-5); Alumina (1344-28-1); Light Aromatic Hydrocarbons (64742-47-8); Mineral Oil (8042-47-5); Glycerin (56-81-5); Triethanolamine (102-71-6)

For more ingredient information, visit www.meguiars.com/ingredients

CHEMTREC (800) 424-9300

Reflect Your Passion™

Formulated by & manufactured for © Meguiar's Inc., Irvine, CA 92618 meguiars.com

MADE IN USA WITH GLOBALLY SOURCED MATERIALS

1-800-347-5700
For free, expert car care advice



PROFESSIONAL

ULTRA-CUT COMPOUND

M105

- ◀ Exclusive, super-mirco abrasive technology
- ◀ Ultra-fast cutting quickly removes 1200 grit or finer sanding marks
- ◀ Super-micro abrasives leave best in class finish

**FOR PROFESSIONAL USE ONLY.
NOT INTENDED FOR RETAIL SALE.**

BODY SHOP SAFE

DIRECTIONS: SHAKE WELL. Always work on a cool, properly cured paint surface. Work one section at a time.

DA Application: Apply directly to appropriate Soft Buff DA Foam Disc. Set DA polisher to 4800 - 5800 OPM. Apply moderate pressure on initial 2-3 passes followed with light pressure for following two passes. Wipe off residue immediately after each panel.

Rotary Application: Set rotary buffer to approximately 1500-2000 RPM's. Use with Meguiar's Wool Pad. Apply directly to the paint surface and begin working in a 2' x 2' area with overlapping passes. Continue working until defects or sanding marks are removed. Wipe remaining residue with a Meguiar's M9910 Ultimate Wipe Microfiber Cloth prior to polishing.

PAINTABLE: Body Shop Safe.

CONTAINS: Water (7732-18-5); Alumina (1344-28-1); Light Aromatic Hydrocarbons (64742-47-8); Mineral Oil (8042-47-5); Glycerin (56-81-5); Triethanolamine (102-71-6)

For more ingredient information, visit www.meguiars.com/ingredients

CHEMTREC (800) 424-9300

Reflect Your Passion™

Formulated by & manufactured for © Meguiar's Inc., Irvine, CA 92618 meguiars.com

MADE IN USA WITH GLOBALLY SOURCED MATERIALS

1-800-347-5700
For free, expert car care advice



PROFESSIONAL

ULTRA-CUT COMPOUND

M105

- ◀ Exclusive, super-mirco abrasive technology
- ◀ Ultra-fast cutting quickly removes 1200 grit or finer sanding marks
- ◀ Super-micro abrasives leave best in class finish

**FOR PROFESSIONAL USE ONLY.
NOT INTENDED FOR RETAIL SALE.**

BODY SHOP SAFE

DIRECTIONS: SHAKE WELL. Always work on a cool, properly cured paint surface. Work one section at a time.

DA Application: Apply directly to appropriate Soft Buff DA Foam Disc. Set DA polisher to 4800 - 5800 OPM. Apply moderate pressure on initial 2-3 passes followed with light pressure for following two passes. Wipe off residue immediately after each panel.

Rotary Application: Set rotary buffer to approximately 1500-2000 RPM's. Use with Meguiar's Wool Pad. Apply directly to the paint surface and begin working in a 2' x 2' area with overlapping passes. Continue working until defects or sanding marks are removed. Wipe remaining residue with a Meguiar's M9910 Ultimate Wipe Microfiber Cloth prior to polishing.

PAINTABLE: Body Shop Safe.