

# RC Structures (1)

**DESIGN FOR FLEXURE, SHEAR AND BOND**

By

Dr. Susumu Kono  
Institute of Innovative Research  
Tokyo Institute of Technology

International Institute of  
Seismology and Earthquake Engineering,  
Building Research Institute

2017

Lecture Note on

# The Performance Based Design of Reinforced Concrete Structures

**DESIGN FOR FLEXURE, SHEAR AND BOND**

By

Dr. Susumu Kono  
Institute of Innovative Research  
Tokyo Institute of Technology

# Table of Contents

<b>1</b>	<b>LOAD-DEFLECTION RELATION OF RC MEMBERS</b>	<b>1</b>
<b>2</b>	<b>DESIGN FOR FLEXURAL CRACKING</b>	<b>2</b>
2.1	Introduction	2
2.2	Basic assumptions	2
2.3	Cracking moment	2
2.3.1	Equivalent moment of inertia	2
2.3.2	Cracking moment	3
2.3.3	Example : Equivalent moment of inertial and the cracking moment	3
2.4	Axial force at cracking	5
2.4.1	Compressive cracking force	5
2.4.2	Tensile cracking force	5
<b>3</b>	<b>DESIGN FOR ULTIMATE FLEXURE</b>	<b>7</b>
3.1	Introduction	7
3.2	Assumptions	7
3.3	Ultimate flexural moment	7
3.3.1	Stress-strain relations of concrete and equivalent stress block	7
3.3.2	Ultimate flexure moment of doubly reinforced concrete beams	9
<b>4</b>	<b>DESIGN FOR SHEAR</b>	<b>13</b>
4.1	Introduction	13
4.2	The Concept of Shear Stresses	14
4.2.1	Shear stress for an elastic and homogeneous member	14
4.2.2	Shear stress for a reinforced concrete member before cracking	15
4.2.3	Shear stress for a reinforced concrete member after cracking	16
4.3	The Mechanism of Shear Resistance in Reinforced Concrete Beams without Web Reinforcement	18
4.3.1	The Formation of Diagonal Cracks	18
4.3.2	Equilibrium in the Shear Span of a Beam	19
4.3.3	The Principal Mechanisms of Shear Resistance	21
4.3.4	Size Effects	28
4.3.5	Shear Failure Mechanisms	29
4.4	The Mechanism of Shear Resistance in Reinforced Concrete Beams with Web Reinforcement	31

4.4.1	The Role of Web Reinforcement	31
4.4.2	The Truss Mechanism	32
<b>5</b>	<b>DESIGN FOR BOND</b>	<b>36</b>
5.1	Introduction	36
5.2	Basic Theory for Bond	36
<b>6</b>	<b>SHEAR DESIGN OF RC MEMBERS BASED ON ‘DESIGN GUIDELINES FOR EARTHQUAKE RESISTANT REINFORCED CONCRETE BUILDINGS BASED ON INELASTIC DISPLACEMENT CONCEPT’ (1997)</b>	<b>39</b>
6.1	Fundamental concept	39
6.1.1	Plastic theory	39
6.2	Design for shear of beams and columns	40
6.2.1	Code equations for shear strength of beams and columns	40
6.2.2	Explanations on shear strength without plastic hinge rotation	42
6.2.3	Truss mechanism at a transition region	49
6.2.4	Reduction of shear capacity due to plastic hinge rotation	50
6.2.5	Validation of the equations	51
6.2.6	Design examples	53
6.3	Design for bond	57
6.3.1	Code equations	57
6.3.2	Effect of bond strength on Shear strength	59
6.3.3	Design examples	59
6.4	Design for shear of shearwalls	63
6.4.1	Shear cracking strength	63
6.4.2	Shear strength and $V$ for a hinge region	63
6.4.3	Design examples	66
<b>7</b>	<b>AIJ STANDARD FOR STRUCTURAL CALCULATION OF REINFORCED CONCRETE STRUCTURES, REVISED IN 1991</b>	<b>68</b>
7.1	Introduction	68
7.2	Design for Shear	68
7.2.1	Art. 16 Shear Reinforcement in Beams and Columns	68
7.3	Design for Development, Anchorage and Lap Splices	75
<b>8</b>	<b>SHEAR DESIGN OF RC MEMBERS BASED ON ‘DESIGN GUIDELINES FOR EARTHQUAKE RESISTANT REINFORCED CONCRETE BUILDINGS BASED ON ULTIMATE STRENGTH CONCEPT’ (1991)</b>	<b>78</b>
8.1	Plastic theory	78

8.1.1	The lower bound theorem	78
8.1.2	The upper bound theorem	78
<b>8.2</b>	<b>Scope</b>	<b>78</b>
<b>8.3</b>	<b>Shear strength of beams and columns</b>	<b>78</b>
8.3.1	The first term (contribution from the truss action)	79
8.3.2	The second term (contribution from the arch action)	80
8.3.3	Integration of the truss and arch actions	80
8.3.4	Coefficients for members without plastic hinges	81
8.3.5	Coefficients for members with plastic hinges	82
8.3.6	Minimum reinforcement	83
<b>8.4</b>	<b>Shear strength of walls</b>	<b>83</b>
8.4.1	Shear strength	83
8.4.2	Equivalent wall widths	83
8.4.3	Effective factor of concrete for a non-hinge region	83
8.4.4	Effective factor of concrete for a hinge region	83
8.4.5	Beam between stories	84
8.4.6	Minimum reinforcement	84
<b>8.5</b>	<b>Bond</b>	<b>84</b>
8.5.1	Design bond stress	84
8.5.2	Bond strength	84
<b>REFERENCES</b>		<b>85</b>
<b>HOW TO REACH US</b>		<b>85</b>

## 1 LOAD-DEFLECTION RELATION OF RC MEMBERS

Concrete is a quasi-brittle material and its deformation capability is limited. However, it is possible to make concrete members ductile as shown in Figure 1.1 by combining brittle concrete with ductile reinforcing steel bars.




Figure 1.1 Moment – curvature relation of a RC beam (6)

## 2 DESIGN FOR FLEXURAL CRACKING

### 2.1 Introduction

Concrete carries tensile force before cracking. The stiffness of members before cracking is higher than that after cracking. This chapters demonstrates how to obtain the cracking moment,  $M_c$ .

### 2.2 Basic assumptions

The following basic assumptions are made to compute the cracking moment,  $M_c$ .

- Bernoulli's theorem is satisfied (plane-sections-remain-plane assumption).
- Stress-strain relation of concrete is elastic.
- Stress-strain relation of reinforcing bars is elastic.
- Concrete carries tensile force.

### 2.3 Cracking moment

#### 2.3.1 Equivalent moment of inertia

Consider the section which has the center of the gravity of the section is located below the half depth by "e" as shown in Figure 2.1(a). Strictly speaking, the moment of inertia of this reinforced concrete section is expressed as:

$$I_{e1} = I_{e3} + (n-1)a_t y_t^2 + (n-1)a_c y_c^2 \quad (2.1)$$

where  $I_{e3}$  is expressed in Eq.

(2.3). If the overlapping of concrete and reinforcement is allowed, the equation can be simplified as:

$$I_{e2} = I_{e3} + na_t y_t^2 + na_c y_c^2 \quad (2.2)$$

Neglect the reinforcement and assume that the whole section is filled with concrete. The moment of inertia about the C.G. is expressed as:

$$I_{e3} = \frac{bD^3}{12} + bDe^2 \quad (2.3)$$




Figure 2.1 A reinforced concrete beam

### 2.3.2 Cracking moment

Stress at the tensile fiber can be expressed as:

$$f_t = \frac{M_c D}{I_e} = \frac{M_c}{Z_e} \quad (2.4)$$

where  $I_e$  is either of  $I_{e1}$ ,  $I_{e2}$  and  $I_{e3}$ .

When the tensile stress reaches the modulus of rupture,  $f_r$ , expressed as follows, the section cracks.

$$f_r = 0.56\sqrt{f'_c} \quad (N/mm^2) \quad (2.5)$$

Hence, the cracking moment can be expressed as:

$$M_c = f_r Z_e \quad (2.6)$$

### 2.3.3 Example : Equivalent moment of inertial and the cracking moment

Let us compute the cracking moment of the doubly reinforced concrete beam in Figure 2.2.

$$\begin{aligned} b &= 400 \text{ mm} \\ d_c &= d_t = 60 \text{ mm} \\ d &= 640 \text{ mm} \\ D &= 700 \text{ mm} \end{aligned}$$

Concrete

$$\text{Compressive strength } f'_c = 24 \text{ MPa}$$

$$\text{Unit weight } \gamma = 24 \text{ kN/m}^3$$




Figure 2.2 Section of a reinforced concrete beam

Reinforcement

$$\text{Tensile reinforcement} \quad \text{SD345 3-D22} \quad a_t = 387 \times 3 = 1161 \text{ mm}^2$$

$$\text{Compressive reinforcement} \quad \text{SD345 3-D22} \quad a_c = 387 \times 3 = 1161 \text{ mm}^2$$

Young's modulus of concrete and reinforcing bars are;

$$\begin{aligned} E_c &= 33500 \times \left(\frac{\gamma}{24}\right)^2 \left(\frac{f'_c}{60}\right)^{\frac{1}{3}} \\ &= 33500 \times \left(\frac{24}{24}\right)^2 \left(\frac{24}{60}\right)^{\frac{1}{3}} \end{aligned} \quad (2.7)$$

$$= 24700 \text{ N/mm}^2 = 24.7 \text{ GPa}$$

$$E_s = 205000 \text{ N/mm}^2 = 205 \text{ GPa} \quad (2.8)$$



Then the modular ratio,  $n$ , is

$$n = \frac{E_s}{E_c} = \frac{205 \text{ GPa}}{24.7 \text{ GPa}} = 8.30 \quad (2.9)$$

The modulus of rupture is:

$$f_r = 0.56\sqrt{f'_c} = 0.56\sqrt{24} = 2.74 \text{ N/mm}^2 \quad (2.10)$$

Strictly, the moment capacity is:

$$\begin{aligned} I_{e1} &= \frac{bD^3}{12} + (n-1)a_t y_t^2 + (n-1)a_c y_c^2 \\ &= \frac{400 \cdot 700^3}{12} + (8.3-1) \cdot 1161 \cdot (350-60)^2 + (8.3-1) \cdot 1161 \cdot (350-60)^2 \\ &= 1.29 \times 10^{10} \text{ mm}^4 \end{aligned} \quad (2.11)$$

$$\begin{aligned} Z_{e1} &= \frac{I_{e1}}{H_t} = \frac{1.29 \times 10^{10} \text{ mm}^4}{350 \text{ mm}} \\ &= 3.69 \times 10^7 \text{ mm}^3 \end{aligned} \quad (2.12)$$

$$\begin{aligned} M_{c1} &= f_r Z_{e1} = 2.74 \text{ N/mm}^2 \cdot 3.69 \times 10^7 \text{ mm}^3 \\ &= 101.2 \text{ kN} \cdot \text{m} \end{aligned} \quad (2.13)$$

If the overlapping of concrete and reinforcement is allowed, the moment capacity is:

$$\begin{aligned} I_{e2} &= \frac{bD^3}{12} + na_t y_t^2 + na_c y_c^2 \\ &= \frac{400 \cdot 700^3}{12} + 8.3 \cdot 1161 \cdot (350-60)^2 + 8.3 \cdot 1161 \cdot (350-60)^2 \\ &= 1.31 \times 10^{10} \text{ mm}^4 \end{aligned} \quad (2.14)$$

$$Z_{e2} = \frac{I_{e2}}{H_t} = \frac{1.31 \times 10^{10} \text{ mm}^4}{350 \text{ mm}} = 3.74 \times 10^7 \text{ mm}^3 \quad (2.15)$$

$$M_{c2} = f_r Z_{e2} = 2.74 \text{ N/mm}^2 \cdot 3.74 \times 10^7 \text{ mm}^3 = 102.6 \text{ kN} \cdot \text{m} \quad (2.16)$$

If reinforcement is neglected, the moment capacity is:

$$I_{e3} = \frac{bD^3}{12} = \frac{400 \cdot 700^3}{12} = 1.14 \times 10^{10} \text{ mm}^4 \quad (2.17)$$

$$Z_{e3} = \frac{I_{e3}}{H_t} = \frac{1.14 \times 10^{10} \text{ mm}^4}{350 \text{ mm}} = 3.27 \times 10^7 \text{ mm}^3 \quad (2.18)$$

$$M_{c3} = f_r Z_{e3} = 2.74 \text{ N/mm}^2 \cdot 3.27 \times 10^7 \text{ mm}^3 = 89.6 \text{ kN} \cdot \text{m} \quad (2.19)$$

It is seen that  $M_{c1}$  and  $M_{c2}$  are nearly same but  $M_{c3}$  is 11.5% less than  $M_{c1}$ .

## 2.4 Axial force at cracking

### 2.4.1 Compressive cracking force

Under concentric compression, cracks do not form.

### 2.4.2 Tensile cracking force

When the stress reaches the tensile strength,  $f'_t$ , the tensile force can be obtained as follows assuming that concrete and reinforcement are elastic.

#### (a) Equilibrium

External and internal forces are equilibrated in axial direction.

$$N = T_c + T_s \quad (2.20)$$

$T_c$  : Tensile resultant force of concrete

$T_s$  : Tensile resultant force of reinforcement

#### (b) Strain compatibility

Strain at the section is uniform and expressed as:

$$\varepsilon_{st} = \varepsilon_c \quad (2.21)$$

#### (c) Stress-strain relation

Since concrete and reinforcement are assumed elastic, stress and strain relations are expressed as:

$$\sigma_c = E_c \cdot \varepsilon_c \quad (\text{concrete}) \quad (2.22)$$

$$\sigma_{st} = E_s \cdot \varepsilon_{st} \quad (\text{reinforcement}) \quad (2.23)$$

Combining Eqs. (2.20) through (2.23) for a column section in ,

$$\begin{aligned} N_c &= A_c E_c \varepsilon_c + a_{st} E_s \varepsilon_{st} \\ &= A_c E_c \varepsilon_c + a_{st} n E_c \varepsilon_c \\ &= bh E_c \varepsilon_c + a_{st} (n-1) E_c \varepsilon_c \\ &= \{bh + a_{st} (n-1)\} E_c \varepsilon_c \end{aligned} \quad (2.24)$$

where n is the section modulus in Eq. (2.9)

When the concrete stress,  $\sigma_c = E_c \cdot \varepsilon_c$ , reaches the cracking strength,  $f'_t$ , a crack forms and the tensile force can be expressed as:

$$N_c = \{bh + a_{st}(n-1)\} f'_t \quad (2.25)$$




Figure 2.3 Section of a reinforced concrete beam

### 3 DESIGN FOR ULTIMATE FLEXURE

#### 3.1 Introduction

It is important to know the ultimate flexural moment capacity at failure and the failure mode when the member is subjected to unexpectedly large load. It should be noted that concrete and reinforcement are not elastic anymore at this stage.

#### 3.2 Assumptions

The following assumptions are made to compute the ultimate flexural strength,  $M_n$ .

- Bernoulli's theorem is satisfied (plane-sections-remain-plane assumption).
- Plastic condition of stress-strain relation of concrete is considered. Concrete stress block indices  $k_1$ ,  $k_2$ ,  $k_3$ , and the ultimate compressive strain,  $\epsilon_{cu}$ , are assumed to be known.
- Elastic-plastic condition of stress-strain relation of reinforcing bars is considered.
- Concrete DOES NOT carry tensile force.

#### 3.3 Ultimate flexural moment

##### 3.3.1 Stress-strain relations of concrete and equivalent stress block

Assuming that the stress-strain relation of concrete is expressed in Figure 3.1, stress block coefficients represent the area under the curve and the location of the centroid.

$k_1 k_3 f'_c \times \epsilon_{cu}$  = equivalent area under the curve

$k_2 \epsilon_{cu}$  = the location of the centroid of the area under the curve in terms of  $\epsilon_{cu}$

- $k_1$  : coefficient to represent the average stress when the compressive fiber reaches the ultimate compressive strain,  $\epsilon_{cu}$ .
- $k_2$  : coefficient to represent the location of centroid of the area under the curve in terms of  $\epsilon_{cu}$ .
- $k_3$  : coefficient to represent the difference in compressive strengths of test cylinders and members

**Table 3.1 Concrete stress block coefficients**

	$f'_c \leq 27.4 \text{ N/mm}^2$	$f'_c > 27.4 \text{ N/mm}^2$
$\epsilon_{cu}$	0.003	
$k_1$	0.85	$0.85 - 0.05(f'_c - 27.4) / 6.84$
$k_2$	0.85	
$k_3$	$0.5 k_1$	




Figure 3.1 Stress – strain relation of concrete in structural members and the meaning of stress block (6)




Figure 3.2 Stress – strain relation of reinforcing bars (6)

### 3.3.2 Ultimate flexure moment of doubly reinforced concrete beams

#### 3.3.2.1 Basic equations

##### (a) Equilibrium

External and internal forces should be equal in terms of axial force and moment.

Equilibrium for axial force

$$N = C_c + C_s - T_s \quad (3.1)$$

Equilibrium for moment

$$M = C_c \cdot (x_n - k_2 x_n) + C_s (x_n - d_c) + T_s (d - x_n) \quad (3.2)$$

##### (b) Strain compatibility

Based on the Bernoulli's theorem, the strain at arbitrary height of the section can be expressed with the ultimate strain of compressive fiber,  $\varepsilon_{cu}$ .

$$\frac{\varepsilon_{st}}{d - x_n} = \frac{\varepsilon_{sc}}{x_n - d_c} = \frac{\varepsilon_{cu}}{x_n} \quad (3.3)$$

##### (c) Stress-strain relation

It is defined that the ultimate flexural moment is reached when the strain at the compressive fiber reaches the ultimate strain ( $\varepsilon_c = \varepsilon_{cu} = 0.003$ ). At this stage, concrete does not follow the elastic relation,  $\sigma_c = E_c \cdot \varepsilon_c$ , anymore. Reinforcement is either elastic ( $\sigma_{st} = E_s \cdot \varepsilon_{st}$ ) or plastic ( $\sigma_{st} = f_y$ ).




Figure 3.3 Ultimate condition of a rectangular reinforced concrete beam

### 3.3.2.2 Depth of the neutral axis, $x_n$

Flexural failure can be categorized into three failure modes; flexural tensile failure, flexural compression failure, and balanced failure. No matter which of three failure modes is taken, the strain at the compressive fiber always reaches the ultimate limit strain,  $\varepsilon_{cu}$ , that is,  $\varepsilon_c = \varepsilon_{cu} = 0.003$ . Hence,  $C_c$ ,  $C_s$ ,  $T_s$  can be computed based on the ultimate strain and the neutral axis depth,  $x_n$ .

Equivalent stress block is used to represent the compressive resultant force of concrete,  $C_c$ .

$$C_c = k_1 k_3 f'_c x_n b \quad (3.4)$$

The compressive resultant force of steel,  $C_s$ , can be computed based on its strain,

$$\varepsilon_{sc} = \frac{x_n - d_c}{x_n} \varepsilon_{cu}.$$

$$C_s = f_y a_c \text{ (yielded) or } C_s = (E_s \varepsilon_{sc}) a_c \text{ (elastic)} \quad (3.5)$$

The tensile resultant force of steel,  $T_s$ , can be computed based on its strain,

$$\varepsilon_{st} = \frac{d - x_n}{x_n} \varepsilon_{cu}, \text{ like } C_s.$$

$$T_s = f_y a_t \text{ (yielded) or } T_s = (E_s \varepsilon_{st}) a_t \text{ (elastic)} \quad (3.6)$$

Substitute into the axial force equilibrium,  $N = C_c + C_s - T_s$  to obtain  $x_n$ .

*Case 1.* When both compressive reinforce and tensile reinforcement have yielded, the equilibrium is:

$$0 = k_1 k_3 f'_c x_n b + f_y a_c - f_y a_t \quad (3.7)$$

*Case 2.* When compressive reinforcement is elastic and tensile reinforcement has yielded, the equilibrium is:

$$0 = k_1 k_3 f'_c x_n b + (E_s \varepsilon_{sc}) a_c - f_y a_t$$

$$0 = k_1 k_3 f'_c x_n b + \left( E_s \frac{x_n - d_c}{x_n} \varepsilon_{cu} \right) a_c - f_y a_t \quad (3.8)$$

*Case 3.* When compressive reinforcement has yielded and tensile reinforcement is elastic, the equilibrium is:

$$0 = k_1 k_3 f'_c x_n b + f_y a_c - (E_s \varepsilon_{st}) a_t$$

$$0 = k_1 k_3 f'_c x_n b + f_y a_c - \left( E_s \frac{d - x_n}{x_n} \varepsilon_{cu} \right) a_t \quad (3.9)$$

*Case 4.* When both compressive reinforce and tensile reinforcement are elastic, the equilibrium is:

$$0 = k_1 k_3 f'_c x_n b + (E_s \varepsilon_{sc}) a_c - (E_s \varepsilon_{st}) a_t$$

$$0 = k_1 k_3 f'_c x_n b + \left( E_s \frac{x_n - d_c}{x_n} \varepsilon_{cu} \right) a_c - \left( E_s \frac{d - x_n}{x_n} \varepsilon_{cu} \right) a_t \quad (3.10)$$

Obtain  $x_n$  for four cases. Recompute the strains of compressive and tensile reinforcements,  $\varepsilon_{sc} = \frac{x_n - d_c}{x_n} \varepsilon_{cu}$  and  $\varepsilon_{st} = \frac{d - x_n}{x_n} \varepsilon_{cu}$  and compare the results with the assumptions. There should be only one case in which the assumption and the result are consistent and this case turns out to be the correct answer. The assumption and the result in other cases are inconsistent and is judged as wrong.

### 3.3.2.3 Ultimate flexural moment capacity, $M_n$

The ultimate flexural moment,  $M_n$ , can be computed using the correct  $x_n$ . When no axial force acts, the moment can be computed about any height of the section. In the computation, the coefficient  $k_2$  is used.

$$M_n = C_c \cdot (x_n - k_2 x_n) + C_s (x_n - d_c) + T_s (d - x_n) \quad (3.11)$$

### 3.3.2.4 Amount of reinforcement for balanced failure

There is a case that the tensile reinforcement yields exactly when strain of concrete at the compression fiber reaches the ultimate strain. This failure is called balanced failure.

### 3.3.2.5 Example of computing the ultimate flexural moment capacity

The ultimate flexural moment for a RC beam in Section 2.3.3 is computed in this section.

Case 2 (compressive reinforcement is elastic and tensile reinforcement has yielded is assumed).

$$\begin{aligned} C_c &= k_1 k_3 f'_c x_n b = 0.85 \cdot 0.85 \cdot 24 \text{MPa} \cdot x_n \cdot 400 \text{mm} \\ C_s &= \left( E_s \frac{x_n - d_c}{x_n} \varepsilon_{cu} \right) a_c = \left( 205 \text{GPa} \frac{x_n - 60 \text{mm}}{x_n} 0.003 \right) 1161 \text{mm}^2 \\ T_s &= f_y a_t = 345 \text{MPa} \cdot 1161 \text{mm}^2 \end{aligned} \quad (3.12)$$

Substitute the above three terms into the equilibrium,  $N = C_c + C_s - T_s$  and solve for  $x_n$ . It is noted that  $N = 0$  since the beam has no axial force.

$$x_n = 59.1 \text{ mm}$$

Strain of the compressive reinforcement is:

$$\varepsilon_{sc} = \frac{x_n - d_c}{x_n} \varepsilon_{cu} = \frac{59.1 \text{mm} - 60 \text{mm}}{59.1 \text{mm}} 0.003 = -0.000042 < -\varepsilon_y = -0.00168 \text{ as assumed.}$$

Strain of the tensile reinforcement is:



$$\varepsilon_{st} = \frac{d - x_n}{x_n} \varepsilon_{cu} = \frac{640\text{mm} - 59.1\text{mm}}{59.1\text{mm}} 0.003 = 0.0294 > \varepsilon_y = 0.00168 \text{ as assumed.}$$

Since the assumptions on the reinforcement strain is satisfied, this case turns out to be right. The force resultants are:

$$\begin{aligned} C_c &= k_1 k_3 f'_c x_n b = 0.85 \cdot 0.85 \cdot 24\text{MPa} \cdot 59.1\text{mm} \cdot 400\text{mm} = 410\text{kN} \\ C_s &= (E_s \varepsilon_{sc}) a_c = 205\text{MPa}(-0.000042) \cdot 1161\text{mm}^2 = -9.915\text{kN} \\ (3.13) \\ T_s &= f_y a_t = 345\text{MPa} \cdot 1161\text{mm}^2 = 401\text{kN} \end{aligned}$$

These terms satisfies the equilibrium,  $N = 0 = C_c + C_s - T_s$ . The ultimate flexural moment can be computed about any height of the section. It is computed about the neutral axis here.

$$\begin{aligned} M_n &= C_c \cdot (x_n - k_2 x_n) + C_s (x_n - d_c) + T_s (d - x_n) \\ &= 410\text{kN}(59.1\text{mm} - 0.425 \cdot 59.1\text{mm}) \\ &\quad + (-9.92\text{kN})(59.1\text{mm} - 60\text{mm}) \\ &\quad + (401\text{kN})(640\text{mm} - 59.1\text{mm}) \\ &= 247\text{kNm} \end{aligned} \tag{3.14}$$

## 4 DESIGN FOR SHEAR

### 4.1 Introduction

It may be said that the behavior and failure mechanisms of reinforced concrete members subjected to pure bending has already been studied sufficiently and understood very well. Also, the behavior of a reinforced concrete member under pure bending can be rationally predicted based on the Bernoulli's theory which uses a simple assumption that **plane sections before bending remain plane after bending**. Therefore, with respect to flexural design concept and methods, there is little disagreement between the design codes of various countries.

On the other hand, progress in the understanding of the behavior and failure mechanisms of members subjected to shear with flexure and/or axial load has been somewhat slow and hundreds of publications speak for the complexity of the problem. Nonetheless, all aspects of shear behavior have not been taken into account in any shear design methods currently used.

Since the data obtained from shear tests scatter more widely than those obtained from flexural tests, in general, the shear strength of a member is estimated more conservatively than the flexural strength in the current design codes. This can be seen from the fact that, in the ACI code as well as others, the semi-empirical equations to calculate the **nominal shear strength** of a member have been derived as to give a line close to the lower bound of the background test data. Also a higher safety factor is used in the design for shear than for flexure. For example, in the ACI code, the **strength reduction factor**  $\phi$  of 0.85 is adopted in the design for shear while  $\phi$  of 0.90 is used for the flexure.

A shear failure of a reinforced concrete member can occur in a brittle manner if the reinforcing details are inadequate. Consequently an attempt must be made to suppress such a failure. In earthquake-resistant structures in particular, heavy emphasis is placed on **ductility**, and for this reason the designer must ensure that a shear failure can never occur. This implies that when ductility is essential, the shear strength of the member must be higher than flexural strength which could possibly develop at an ultimate state, even if a frame analysis indicates that the maximum moment induced in the member under design loads does not reach to the flexural strength of the member. This design concept has been typically introduced in the **Capacity Design** of the New Zealand Code (**NZS3101:1995**).

It is still expedient to use the classical concepts of shear stresses in homogeneous, isotropic, elastic bodies when predicting initial crack formation. However, with the development of cracks an extremely complex pattern of stresses ensues, and it becomes difficult to predict precisely the actual behavior of the member. To solve this problem, extensive experimental and theoretical work, particularly in recent years, has greatly extended the identification of various shear resisting mechanisms. Thus the approach to the design for shear in reinforced concrete has been significantly improved in the design codes of various countries.

In this class note, basic theories for shear and bond are briefly reviewed and then shear design methods adopted in the **ACI 318-08** code, the **AIJ Standard** based on allowable stress design (1999) and the **AIJ Design Guidelines** based on inelastic displacement concept (1997) are to be introduced.

## 4.2 The Concept of Shear Stresses

The following text was composed by extracting passages from the book entitled “Reinforced Concrete Structures” by R. Park and T. Paulay published by John Wiley & Sons, Inc. in 1975, with modifications. It is old from the viewpoint of the published year but still the best book to understand the background of the shear design concepts and the methods adopted in the current design codes of various countries.

### 4.2.1 Shear stress for an elastic and homogeneous member

Consider a simply supported beam under loading as shown in Figure 4.1(a). Equilibrium condition in horizontal direction for the free body in Figure 4.1(f) is

$$v(y) \cdot b(y) \cdot dx = dT(y) \quad (4.1)$$




Figure 4.1 Shear stress for elastic and homogeneous member

where  $v(y)$  is the shear stress,  $b(y)$  is the section width, and  $T(y)$  is the tension resultant action on the shaded free body. The increment in  $T(y)$  at distance  $dx$  is  $dT(y)$  and it can be expressed as:

$$\begin{aligned} dT(y) &= \int_{-h/2}^y d\sigma(y) \cdot b(y) dy = \int_{-h/2}^y \frac{dM(x)}{I(x)} y \cdot b(y) dy \\ &= \frac{dM(x)}{I(x)} \int_{-h/2}^y y \cdot b(y) dy = \frac{dM(x)}{I(x)} S(y) \end{aligned} \quad (4.2)$$

where  $I(x)$  is the second moment of inertia and  $S(y)$  is the first moment of inertia about  $y=0$  where the center of gravity locates. From Eqs. (4.1) and (4.2),

$$v(y) = \frac{dT(y)}{b(y) \cdot dx} = \frac{dM(x) \cdot S(y)}{b(y) \cdot dx \cdot I(x)} = \frac{V(x) \cdot S(y)}{b(y) \cdot I(x)} \quad (4.3)$$

For a prismatic beam with a rectangular section,  $v(y=0) = \frac{3V(x)}{2bh}$  can be obtained from  $S(y=0) = \frac{bh}{2} \cdot \frac{h}{4} = \frac{bh^2}{8}$  and  $I(x) = \frac{bh^3}{12}$

#### 4.2.2 Shear stress for a reinforced concrete member before cracking

Using the notation in Figure 4.2, the equilibrium of the shaded part of the beam element will be satisfied when the horizontal shear stress is

$$v(y) = \frac{V(x) \cdot S(y)}{b(y) \cdot I(x)} \quad (4.4)$$

Since the distance between the compression and tension resultants,  $z$ , is expressed as

$$z(x, y) = \frac{I(x)}{S(y)} \quad (4.5)$$

Hence,

$$v(y) = \frac{V(x)}{b(y) \cdot z(x, y)} \quad (4.6)$$

It is seen that the stress state before cracking is identical to the state in Section 4.2.1.

#### 4.2.3 Shear stress for a reinforced concrete member after cracking

Consider a reinforced concrete beam with cracking as shown in Figure 4.3. The equilibrium of an arbitrary free body located below the neutral axis is written as:

$$\begin{aligned}
 b_w(y) \cdot dx \cdot v(y) &= dT(x) \\
 v(y) &= \frac{1}{b_w(y)} \frac{dT(x)}{dx} \\
 &= \frac{1}{b_w(y)} \frac{d(M / jd)}{dx} \quad \left\{ \begin{array}{l} \text{Assume that } jd = \text{constant} \end{array} \right. \\
 &= \frac{1}{b_w(y)jd} \frac{dM}{dx} \\
 &= \frac{V}{b_w(y)jd}
 \end{aligned}
 \tag{4.7}$$

or

$$q = v(y) \cdot b_w(y) = \frac{dT(x)}{dx} = \frac{V}{jd}
 \tag{4.7}'$$

where  $q$  is the bond force per unit length of the member and termed shear flow.

As Figure 4.3 shows, the horizontal force transferred across the cracked zone of the section remains constant; hence the shear flow in the tension zone is constant. It is evident that shear stress depends on the width of the web, illustrated for a particular example in Figure 4.3. Since the concrete below the neutral axis (NA) is assumed to be in a state of pure shear, this equation has been used as the measure of diagonal tension in the cracked tension zone of a reinforced concrete beam. This also implies that vertical shear stresses are transmitted in this fashion across sections, irrespective of the presence of flexural cracks.

In many design codes including the AIJ Standard, this traditional shear stress equation is still used. **It is a convenient "index" to measure shear intensity**, but it cannot be considered as a shear stress at any particular locality in a cracked reinforced concrete beam. For convenience the ACI adopted, as an index of shear intensity, the simple equation

$$v = \frac{V}{b_w d}
 \tag{4.8}$$

In certain cases, the maximum shear stress could occur at a fiber other than at the web of the section. When the flange of a T section carries a large compression force, as over the shaded area to the right of section 1 in Figure 4.3, the shear at the flange-web junction may become critical, and horizontal reinforcement in the flange may be

needed. In beams supporting floors of buildings, the flexural reinforcement in the slab is usually adequate for this purpose.




Figure 4.2 Shear force, shear flow, and shear stresses in a homogeneous isotropic elastic beam




Figure 4.3 Shear stress across an idealized cracked reinforced concrete section

### 4.3 The Mechanism of Shear Resistance in Reinforced Concrete Beams without Web Reinforcement

---

-

In practical design, web reinforcement is normally required to be provided for beams in the form of stirrups. Hence, you may wonder why the mechanism of shear resistance in beams without web reinforcement is discussed in the following sections. The reason may be explained as follows. The shear strength of beams provided by so-called beam action and arch action could be identified through the study for the case of beams without web reinforcement. Also, based on such studies, the most of the current design codes assess the contribution of concrete to the shear resistant capacity of reinforced concrete members. For example, in the ACI code, the nominal shear strength of beams,  $V_n$ , is calculated as the sum of the strength provided by concrete,  $V_c$ , and that by shear reinforcement  $V_s$ , that is,  $V_n = V_c + V_s$ . In this equation,  $V_c$  is calculated using the empirical equations obtained from the shear tests on beams without shear reinforcement.

---

#### 4.3.1 The Formation of Diagonal Cracks

In a reinforced concrete member, flexure and shear combine to create a biaxial state of stress. Cracks form when the principal tensile stresses reach the tensile strength of the concrete. In a region of large bending moments, these stresses are greatest at the extreme tensile fiber of the member and are responsible for the initiation of flexural cracks perpendicular to the axis of the member. In the region of high shear force, significant principal tensile stresses, also referred to as **diagonal tension**, may be generated at approximately 45 degree to the axis of the member as can be seen in Figure 4.4. These may result in inclined (diagonal tension) cracks. With few exceptions these inclined cracks are extensions of flexural cracks. Only in rather special cases, as in webs of flanged beams, are diagonal tension cracks initiated in the vicinity of the neutral axis. The principal stress concept is of little value in the assessment of subsequent behavior unless the complex distribution of stresses in the concrete after cracking is considered. Either a reinforced concrete flexural member collapses immediately after the formation of diagonal cracks, or an entirely new shear carrying mechanism develops which is capable of sustaining further load in a cracked beam.

The diagonal cracking load originating from flexure and shear is usually much smaller than would be expected from principal stress analysis and the tensile strength of concrete. This condition is largely due to

1. the presence of shrinkage stresses,
2. the redistribution of shear stresses between flexural cracks, and
3. the local weakening of a cross section by transverse reinforcement, which causes a regular pattern of discontinuities along a beam.

In the early stages of reinforced concrete design, diagonal cracking was considered to be undesirable. However, it is now recognized that diagonal cracking under service load conditions is acceptable, provided that crack widths remain within the same limits accepted for flexure.




Figure 4.4 Trajectories of principal stresses in a homogeneous isotropic beam

#### 4.3.2 Equilibrium in the Shear Span of a Beam

Figure 4.5(a) shows part of a simply supported beam over which the shear force is constant. The internal and external forces that maintain equilibrium for this free body, bounded on one side by a diagonal crack, can be identified. It may be seen that the total external transverse force  $V$ , is resisted by the combination of

1. a shear force across the compression zone  $V_c$ ,
2. a dowel force transmitted across the crack by the flexural reinforcement  $V_d$ , and
3. the vertical components of inclined shearing stresses  $v_a$  transmitted across the inclined crack by means of interlocking of the aggregate particles.

$$V_a = \left( \sum v_a \right) \cdot \sin \alpha$$

To simplify the equilibrium statement, we assume that shear stresses transmitted by aggregate interlock can be lumped into a single force  $G$ , whose line of action passes through two distinct points of the section (see Figure 4.5(b)). With this simplification the force polygon in Figure 4.5(c) represents the equilibrium of the free body. This condition can also be stated in the form

$$V = V_c + V_a + V_d \quad (4.9)$$

representing the contribution of the compression zone, aggregate interlock, and dowel action to shear resistance in a beam without web reinforcement.



The moment of resistance of the beam is expressed by

$$M_{(x)} = x \cdot V_{(x)} = (T_{(x-jd \cdot \cot \alpha)} + V_{d(x-jd \cdot \cot \alpha)} \cdot \cot \alpha) \cdot jd \quad (4.10)$$

If the contribution of the dowel force toward flexural resistance is ignored (a justifiable step for design purposes, particularly in the absence of stirrups the moment of resistance simplifies to

$$M_{(x)} = T_{(x-jd \cdot \cot \alpha)} \cdot jd \quad (4.11)$$

It is important to note that the moment and the tension force, related to each other in Figure 4.5(b) and Eq. (4.11), do not occur at the same cross section of the beam. It is seen that the tension in the flexural reinforcement at distance  $(x - jd \cot \alpha)$  from the support is governed by the moment at a distance  $x$  from the support of the beam. The increase in the steel stresses clearly depends on the slope of the idealized diagonal crack. When  $\alpha$  is a little less than 45 degree,  $jd \cot \alpha$  is nearly equal to  $d$ . This must be taken into account when the curtailment of the flexural reinforcement is determined (see Eq. 28 in Art .17 of the AIJ Standard 1991).




Figure 4.5 Equilibrium requirements in the shear span of a beam

### 4.3.3 The Principal Mechanisms of Shear Resistance

When the relationship between the external moment and the internal moment of resistance given by Eq. (4.11) are combined with the well-known relationship between shear and the rate of change of bending moment along a beam, the following modes of internal shear resistance result:

$$V = \frac{dM}{dx} = \frac{d(Tjd)}{dx} = jd \frac{dT}{dx} + T \frac{d(jd)}{dx} \quad (4.12)$$

Beam action	Arch action
----------------	----------------

The term  $jd(dT/dx)$  expresses the behavior of a true prismatic flexural member in which the internal tensile force  $T$  acting on a constant lever arm  $jd$  changes from point to point along the beam, to balance exactly the external moment intensity. **The term  $dT/dx$ , the rate of change of the internal tension force, is termed the bond force,  $q$ ,** applied to the flexural reinforcement per unit length of beam. (See also Figure 4.3). If the internal lever arm remains constant (a normally accepted assumption of the elastic theory analysis of prismatic flexural members) so that  $d(jd)/dx = 0$ , the equation of perfect "**beam action**" is obtained thus

$$V = jd \frac{dT}{dx} = qjd \quad (4.13)$$

The same result was obtained in Eq. (4.7)', where  $q$ , the **bond force per unit length of the member at and immediately above the level of the flexural reinforcement, was termed the shear flow.** It is evident that such simplification of behavior is possible only if the shear flow or bond force can be efficiently transferred between the flexural reinforcement and the concrete surrounding it. It gives rise to the phenomenon of bond.

When for any reason the bond between steel and concrete is destroyed over the entire length of the shear span, the tensile force  $T$  cannot change, hence  $dT/dx = 0$ . Under such circumstances the external shear can be resisted only by inclined internal compression. This extreme case may be termed "**arch action**". Its shear resistance is expressed by the second term on the right-hand side of Eq. (4.12), namely,

$$V = T \frac{d(jd)}{dx} = C \frac{d(jd)}{dx} \quad (4.14)$$

Here the internal tension  $T$  is replaced by the internal compression force  $C$ , **to signify that it is the vertical component of a compression force,** with constant slope, which balances the external shear force.

In a normal reinforced concrete beam in which (owing to slip, cracking, and other causes) the full bond force  $q$  required for beam action cannot be developed, the two mechanisms, as expressed by Eq. (4.12), will offer a combined resistance against shear forces. **The extent, to which each mechanism contributes to shear resistance at various levels of external load intensity, depends on the compatibility of deformations associated with these actions.**

#### 4.3.3.1 Beam Action in the Shear Span

Cracks induced by load on a simply supported beam divide the tension zone into a number of blocks (see crack patterns in Figure 4.7). Each of these blocks may be considered to act as a cantilever with its base at the compression zone of the concrete and its free end just beyond the flexural tension reinforcement. Because of the analogy, the blocks will be referred to as **"concrete cantilevers."** (These cantilevers were called **"comb teeth"** in the paper entitled "The Riddle of Shear Failure and Its Solution" by G. N. J. Kani, Journal of ACI, Proc. Vol.61, No.4, April 1964, pp.441-467)

It was shown in Eq. (4.13) that for perfect beam action to take place, the full bond force  $q$  must be effectively resisted. It remains to be seen how the concrete cantilevers can fulfill such a requirement. The resistance may be examined in more detail if we first identify all the actions to which a typical cantilever is subjected. The components of the cantilever action (see Figure 4.6) are as follows:

1. The increase of the tensile force in the flexural reinforcement between adjacent cracks produces a bond force,  $\Delta T = T_1 - T_2$ .
2. Provided shear displacements occur at the two faces of a crack, shear stresses  $v_{a1}$  and  $v_{a2}$  may be generated by means of aggregate interlocking.
3. The same shear displacements may also induce dowel forces  $V_{d1}$  and  $V_{d2}$  across the flexural reinforcement.
4. At the "built-in" end of the cantilever, an axial force  $P$ , a transverse shearing force  $V_h$ , and a moment  $M_c$  are induced to equilibrate the above-mentioned forces on the cantilever.




Figure 4.6 Actions on a concrete cantilever in the shear span of a beam

It will be noticed that the cantilever moment exerted by the bond force,  $\Delta T$ , is resisted by dowel and aggregate interlock forces in addition to the flexural resistance of  $M_c$  of the concrete. Tests by R.C. Fenwick and T. Paulay have enabled a quantitative comparison between these three modes of cantilever resistance. The flexural resistance of the concrete depends largely on the tensile strength of the concrete, the stress pattern resulting from the actions of  $P$ ,  $V_h$ , and  $M_c$  (see Figure 4.6), and the depth  $s_c$  of the critical cantilever section. The depth  $s_c$  is often quite small, particularly at advanced stages of cracking. Beam 5 in Figure 4.7, which shows a series of beams tested by Leonhardt and Walther, is a good example of this phenomenon. Experiments conducted by R.C. Fenwick and T. Paulay have indicated that **in beams of normal dimensions at the most 20% of the bond force could be resisted by flexure at the "built-in end" of the concrete cantilevers.**

When shear displacement along an inclined crack occurs, a certain amount of shear will be transferred by means of the dowel action of the flexural reinforcement. Where the bars bear against the cover concrete, the dowel capacity will be limited by the tensile strength of the concrete. Once a splitting crack occurs, the stiffness, hence the effectiveness, of the dowel action is greatly reduced. This splitting also adversely affects the bond performance of the bars. The splitting strength of the concrete in turn will depend on the effective concrete area between bars of a layer across which the tension is to be resisted. Of particular importance is the relative position of a bar at the time the concrete is cast. Because of increased sedimentation and water gain under top-cast bars, they require considerably larger shear displacements than bottom-cast bars of a beam to offer the same dowel resistance. **The basic mechanism of dowel action across the shear interface is illustrated in Figure 4.8.**

Tests by H. P. J. Taylor and by R.C. Fenwick and T. Paulay indicated that in beams without web reinforcement the contribution of **dowel action does not exceed 25%** of the total cantilever resistance. However, **dowel action is more significant when stirrup reinforcement is used because a flexural bar can more effectively bear against a stirrup that is tightly bent around it.** Nevertheless, cracks will develop approximately parallel to the flexural bars before the stirrups contribute to carrying dowel forces. The stiffness of the dowel mechanism depends greatly on the position of a crack relative to the adjacent stirrups which would be capable of sustaining a dowel force. Taylor, Baumann and Rüsçh, and others have studied the characteristics of dowel action in beams with pre-formed smooth diagonal cracks. **Qualitative load-displacement relationships for dowel action are presented in Figure 4.9.** When the shear displacement is large enough, and the flexural bars are firmly supported on stirrups, dowel forces can be transferred by kinking of the bars as studied by A. J. O'Leary. This is particularly relevant within **plastic hinges where the flexural reinforcement has yielded or along joints where sliding shear can occur.**




Figure 4.7 Crack pattern in beams tested by Leonhardt and Walther




Figure 4.8 The mechanism of dowel action across a shear interface




Figure 4.9 General dowel shear-dowel displacement relationship

When the two faces of a flexural crack of moderate width are given a shear displacement to each other, a number of coarse aggregate particles projecting across such a crack will enable small shear forces to be transmitted. Clearly among many variables, the width and coarseness of the crack, the shear displacement, and the strength of embedment (i.e., concrete strength), are likely to be the most important. Surprisingly, a very considerable force can be transmitted this way. Measurements on test beams without web reinforcement (conducted by H. P. J. Taylor and by R.C. Fenwick and T. Paulay) indicated that **50 to 70% of the bond force, acting on the concrete cantilever shown in Figure 4.6, was resisted by the aggregate interlock mechanism.** Fenwick demonstrated this convincingly by comparison with a beam in which the aggregate interlock mechanism across smooth pre-formed cracks was eliminated.

The maximum capacity of the **three mechanisms of beam action** (dowel action, aggregate interlock, and the flexural strength of the fixed end of the cantilever) **are not necessarily additive when failure is imminent.** The advance of inclined cracks toward the compression zone reduces the “fixed end” of the cantilever considerably. This results in the large rotations, particularly at the “free end” of the cantilever, which means that the **dowel capacity can be exhausted.** The formation of dowel cracks and secondary diagonal cracks near the reinforcement, visible particularly in beam 8/1 of Figure 4.7, affects the aggregate interlock action, which at this stage carries most of the load.

A sudden reduction of the aggregate interlock force, such as  $\sum v_{a2}$  in Figure 4.6, on one side of the cantilever causes imbalance. Such tensile forces normally lead to further crack propagation, while it cannot be seen in slender beams. This is referred to as **diagonal tension failure.** It is particularly undesirable because it usually occurs very suddenly. Beams 7/1 and 8/1 (Figure 4.7) are good examples of the failure of the beam action in the shear span.

We customarily refer to the shear strength of the compression zone of a beam, on the assumption that aggregate interlock and dowel actions are not viable means of shear resistance. However, recent experiments have shown again that this is not the case. Taylor examined the compression zones of the concrete above diagonal cracks and found that the shear carried in this area ( $V_c$  in Figure 4.5) **increased slowly to a maximum of 25 to 40 %** of the total shear force across the section as the beams approached failure. The remainder of the shear must therefore be carried below the neutral axis in the tension zone of the beam. After the breakdown of the aggregate interlock and the dowel mechanisms, the compression zone is generally unable to carry the increased shear, in addition to the compression force resulting from flexure, and the beam fails.

#### 4.3.3.2 Arch Action in the Shear Span

**The second term of Eq. (4.12) signifies that shear can be sustained by inclined compression in a beam, as illustrated in Figure 4.10.** Arch action requires substantial horizontal **reaction at the support**, which is provided by the flexural reinforcement in a simply supported beam. This imposes heavy demands on the anchorage, and indeed it accounts for the **most common type of arch failure.** In the idealized beam of Figure 4.10, full anchorage is assumed, thus a constant tensile force can develop in the bottom reinforcement over the full length as required. The shaded area indicates the extent of compressed concrete outside which cracks can form. By considering requirements of strain compatibility, and by assuming linear strain distribution across the full concrete section, a unique position of the line of thrust may be determined. The total extension of the reinforcement between anchorages must equal the total elongation of the concrete fiber situated at the same level. Where the concrete is cracked, the elongation can be derived from linear extrapolation of the strains in the compression zone. **Having satisfied these criteria, the translational displacement of the steel relative to surrounding concrete (i.e., the slip), can be determined. A typical slip distribution along the shear span is shown in Figure 4.10.**




Figure 4.10 Slip associated with arch action in an idealized beam

Three points worth noting emerged from the study of such an idealized beam.

1. **Arch action can only occur at the expense of slip** (i.e., of complete loss of bond transfer).
2. The translational displacements required for complete arch action increase toward the **load point and attain a value approximately equal to the total extension of the steel** in the shear span.
3. In the vicinity of the load point the line of thrust, hence **the neutral axis, rises well above the position predicted by standard flexural theory.**

In real beams, particularly when deformed bars are used, no appreciable slip can take place between steel and concrete. The translational displacement occurs mainly as a result of

1. **the flexural deformation or the failure of the concrete cantilevers formed between diagonal cracks and**
2. **the bending of the compression zone above the top of these cracks.**

Also in a real beam, **the transition from beam action to arch action is gradual**, and this can be determined if the development of the tension force along the reinforcement, hence the variation of the internal lever arm in test beams, is observed. **The full strength of arch and beam actions cannot be combined** because of the gross incompatibility of the deformations associated with the two mechanisms.

The available strength from arch action is largely dependent on whether the resulting diagonal compression stresses can be accommodated. For given steel force and beam width, the intensity of the diagonal compression stresses depends on the inclination of the line of thrust. **The shear span to depth ratio ( $a/d$  in Figure 4.10) is a measure of this inclination.** It can also be expressed in terms of the moment and the shear as follows:

$$\frac{a}{d} = \frac{Va}{Vd} = \frac{M}{Vd} \quad (4.15)$$

In the AIJ Standard, the above factor is expressed as  $\frac{M}{Qd}$ , see  $\alpha = \frac{4}{\frac{M}{Qd} + 1}$  in AIJ -Eq.

22 (Section 7.2.1 in this classnote).

Excluding loss of anchorage, arch failures may be placed in three groups.

1. **After the failure of the beam action**, the propagation of an inclined crack reduces the compression zone excessively. A slope is reached when the available area of concrete in the vicinity of the load point becomes too small to resist the compression force and it crushes. This is known as a “**shear**”



- compression failure**". Beams 4, 5, and 6 of Figure 4.7 are good examples of such a failure.
2. The line of thrust may be so eccentric that a **flexural tension failure** occurs in the "compression zone." An example of such behavior is beam 7/1 in Figure 4.7. The failure is very sudden.
  3. When the line of thrust is steeper (i.e., when  $a/d$  is less than 2), considerable reserve strength may be available owing to more efficient arch action. Failure may eventually be due to **diagonal compression crushing or splitting**, which can be likened to a transverse splitting test performed on a standard concrete cylinder (see beam 1 in Figure 4.7). Frequently the flexural capacity of a beam is attained because the arch mechanism is sufficient to sustain the required shear force (see beam 2 in Figure 4.7).

It is important to note that arch action in beams without web reinforcement can occur only if loads are applied to the compression zone of the beam. This was the case for all the test beams in Figure 4.7. The load situation may be more serious when a girder supports secondary beams near its bottom edge. It is evident that effective arch action cannot develop in a beam when the external shear force is transmitted to the tension zone. The arch action must be the dominant mode of shear resistance in deep beams loaded in the compression zone.

#### 4.3.4 Size Effects

For obvious reasons most shear tests have been carried out on relatively small beams. Recently it has been found that the results of such laboratory tests cannot be directly applied to full size beams. The shear strength of beams without web reinforcement appears to decrease as the effective depth increases as shown in Figure 4.11. Kani, in his experiments, has demonstrated this very effectively. If proper scaling of all properties is taken into account, the effect of the absolute size of a beam on its shear strength is not so large. Dowel and aggregate interlock actions in particular can be considerably reduced in large beams if aggregate and reinforcing bar sizes are not correctly scaled. Experiments at the University of Stuttgart indicated, however, that the relative loss of shear strength of large beams was not significant when beams with web reinforcement were compared.

---

M. P. Collins, University of Toronto, has conducted shear tests using large scale beams with section of, for example, 295mm × 1,000 mm. He pointed out that:

1. As a reinforced concrete element is scaled up in size, the crack spacings and hence the crack widths, will increase.
  2. An increase in the crack width will reduce the average tensile stress that can be carried in the cracked concrete, and hence will reduce the shear stress at failure.
  3. This effect is still ignored in many country codes.
-




Figure 4.11 Shear stress at failure as a function of the shear span to depth ratio

#### 4.3.5 Shear Failure Mechanisms

Shear failure mechanisms of simply supported beams, loaded with point loads of the types previously described, fall into three approximate bands of  $a/d$  ratios. These can be observed on the beams tested by Leonhardt and Walther (Figure 4.7). The failure moments and the ultimate shear forces for the 10 beams of Figure 4.7 are plotted against the shear span to depth ratio in Figure 4.12. The beams contained no stirrups and the material properties of all specimens were nearly identical.

- I. Failure of the beam mechanism at or shortly after the application of the **diagonal cracking load**, when  $3 < a/d < 7$ . The subsequent arch mechanism is not capable of sustaining the cracking load.
- II. **Shear compression or flexural tension failure of the compression zone** above diagonal cracking load. This is usually a failure of arch action when  $2 < a/d < 3$ .
- III. **Failure by crushing or splitting of the concrete** (i.e., a failure of arch action), when  $a/d < 2.5$ .

Figure 4.12 reveals that when  $1.5 < a/d < 7$ , the flexural capacity of the beams is not attained. Hence shear governs the design.

By considering the beam action of shear resistance, as outlined previously, it becomes clear that the magnitude of the bond force,  $\Delta T$ , transmitted between two adjacent cracks, is limited by the strength of the cantilever block (Figure 4.6) formed between the cracks. By assuming that the strength of each cantilever in the shear span

of a prismatic beam is the same,  $\Delta T_{max} = q_{max} \Delta x$ , the maximum moment that can be developed by beam action becomes

$$M_{max} = jdT_{max} = jd \sum (q_{max} \Delta x) = q_{max} (jd) x \tag{4.16}$$

where  $q_{max}$  is the maximum bond force per unit length of beam,  $\Delta x$  is the distance between cracks and  $x$  is the distance of the maximum moment section from the support. When this moment is less than the flexural strength of the section  $M_u$ , shear strength associated with beam action governs the capacity of the beam. From Eq. (4.16) it is evident that the moment sustained by the concrete cantilevers of the beam action in the shear span increases with the distance  $x$  from the support. Beam action also implies constant shear strength, limited by  $q_{max}$ , which is independent of the shear span to depth ratio  $a/d$ .

The flexural and shear capacity of beam action are designated by dashed lines in Figure 4.12. When compared with observed ultimate values, they demonstrate that beam action governs the behavior when  $a/d$  is larger than 3. When  $a/d$  is larger than 7, the shear strength exceeded the flexure strength of these beams; hence flexure governs their strength. The discrepancy between the theoretical flexural capacity and the observed shear strength of these beams is indicated by the shaded area in Figure 4.12. The flexural steel content for the beams represented in Figure 4.12 was 2%.




Figure 4.12 Moments and shears at failure plotted against shear span to depth ratio

## 4.4 The Mechanism of Shear Resistance in Reinforced Concrete Beams with Web Reinforcement

### 4.4.1 The Role of Web Reinforcement

The inclusion of web reinforcement such as stirrups does not change fundamentally the previously described mechanism of shear resistance. The concrete cantilevers, which are the principal elements of the beam mechanism, will act as tied cantilevers. In addition to the bond force,  $\Delta T$ , resisted by the combination of aggregate interlock, dowel, and flexural actions of the cantilevers, another bond force  $\Delta T'$  can be sustained by what is traditionally termed "**truss action**". In this truss, the cantilevers act as diagonal compression members (see Figure 4.13).

The presence of stirrups is beneficial to beam action in a number of other aspects, as well. Stirrups contribute to the strength of the shear mechanisms by the following means:

1. Improving the contribution of the dowel action. A stirrup can effectively support a longitudinal bar that is being crossed by a flexural shear crack close to a stirrup.
2. Suppressing flexural tensile stresses in the cantilever blocks by means of the diagonal compression force  $C_d$ , resulting from truss action.
3. Limiting the opening of diagonal cracks unless stirrup steel yields, thus enhancing and preserving shear transfer by aggregate interlock.
4. Providing confinement, when the stirrups are sufficiently closely spaced, thus increasing the compression strength of localities particularly affected by arch action.
5. Preventing the breakdown of bond when splitting cracks develop in anchorage zones because of dowel and anchorage forces.

It may be said that suitably detailed web reinforcement will preserve the integrity, therefore the strength, of the previously defined beam mechanism  $V_c$ , allowing additional shear forces  $V_s$  to be resisted by the truss mechanism.




Figure 4.13 Concrete cantilevers acting as struts

#### 4.4.2 The Truss Mechanism

The analogy between the shear resistance of a parallel chord truss and a web-reinforced concrete beam is an old concept of concrete structures. The analogy, postulated by Mörsch at the beginning of the century, implies that the web of the equivalent truss consists of stirrups acting as tension members and concrete struts running parallel to diagonal cracks, generally at 45 degree to the beam axis. The flexural concrete compression zone and the flexural reinforcement form the top and bottom chords of this analogous pin-jointed truss. The forces in the truss can be determined from considerations of equilibrium only. The behavior of the truss is similar to the previously defined "perfect beam action" to the extent that it can sustain discrete bond forces  $\Delta T'$  at the hypothetical pin-joints along the flexural reinforcement, thus resisting variable external moments on a constant internal lever arm.

The deformations associated with beam or arch action and the truss mechanism within the beam are not compatible. This strain incompatibility, traditionally ignored, becomes progressively less significant as ultimate (i.e., plastic) conditions are approached.




Figure 4.14 Internal forces in an analogous truss

The analogous truss appearing in Figure 4.14 depicts the general case of web reinforcement inclined at an angle  $\beta$  to the horizontal. It will serve to illustrate the relation between the external shear force  $V_s$ , to be resisted by the truss, and the various internal forces. The diagonal compression struts, resisting a force  $C_d$ , are inclined at an angle  $\alpha$  to the horizontal. From the equilibrium force polygon drawn for joint  $X$  in Figure 4.14, it is evident that

$$V_s = C_d \sin \alpha = T_s \sin \beta \quad (4.17)$$

where  $T_s$  is the resultant of all stirrup forces across the diagonal crack. The web steel force per unit length of beam is  $T_s/s$ , where from the geometry of the analogous truss, the spacing between stirrups is

$$s = jd(\cot \alpha + \cot \beta) \quad (4.18)$$

From Eqs. (4.17) and (4.18), the stirrup force per unit length is

$$\frac{T_s}{s} = \frac{V_s}{jd \sin \beta (\cot \alpha + \cot \beta)} = \frac{A_v f_s}{s} \quad (4.19)$$

where  $A_v$  is the area of the web reinforcement spaced at a distance,  $s$ , along the beam and  $f_s$  is the stirrup stress.

For design purposes it is convenient to express shear in terms of nominal stresses. The total shear  $V_u$  is assumed to be resisted partly by the truss mechanism ( $V_s$ ) and partly by the previously described beam or arch mechanisms ( $V_c$ ). In terms of stresses, this is expressed as

$$V_u = V_c + V_s \quad (4.20)$$

where

$$v_s = \frac{V_s}{b_w jd} \approx \frac{V_s}{b_w d} \quad (4.21)$$

Combining Eqs. (4.19) and (4.21), the required area of web reinforcement at ideal strength, when  $f_s = f_y$  becomes

$$A_v = \frac{v_s}{\sin \beta (\cot \alpha + \cot \beta)} \frac{s b_w}{f_y} \quad (4.22)$$

The diagonal compression force  $C_d$  is assumed to generate uniform stresses in the struts of the truss. The struts have an effective depth of  $s' = s \sin \alpha = jd \sin \alpha (\cot \alpha + \cot \beta)$ . Thus the diagonal compression stresses due to the truss mechanism can be approximated by

$$f_{cd} = \frac{C_d}{b_w s'} = \frac{V_s}{b_w jd \sin^2 \alpha (\cot \alpha + \cot \beta)} = \frac{v_s}{\sin^2 \alpha (\cot \alpha + \cot \beta)} \quad (4.23)$$

For the case of vertical stirrups,  $\beta = 90$  degree, and compression diagonals at  $\alpha = 45$  degree, Eqs. (4.22) and (4.23) can be simplified as follows:

$$A_v = v_s \frac{s b_w}{f_y}$$

$$f_{cd} = 2v_s \quad (4.22)'$$

$$(4.23)'$$

The slope of the compression diagonals has been traditionally assumed to be 45 degree to the beam axis. It has been observed, however, that the slope of the diagonal cracks at the boundaries of the struts vary along the beam. Studies based on strain energy considerations show that the optimum angle of the struts is about 38 degree. From Eq. (4.22) it is evident that the web steel demand is reduced as the angle of the compression diagonals becomes less than 45 degree, because more stirrups are encountered across a flat crack. This is often the case, and design equations based on compression struts at 45 degree are conservative. On the other hand, the struts are steeper in the vicinity of point loads. However, in these areas local arch action boosts the capacity of the other shear carrying mechanisms. Generally in a beam having high concrete strength and low web steel content, representing a less rigid tension system, the compression struts are at an angle less than 45 degree, hence the stirrups are more effective than in a 45 degree truss. Conversely with large web steel content and low concrete strength, the load on the concrete will be relieved at the expense of larger stirrups participation.

When assessing the compression strength of the web of beams, it is necessary to consider the following additional factors:

1. The diagonal struts are also subjected to bending moments if they participate in beam action (see Figure 4.6). Secondary moments are introduced because of the absence of true "pin joints" in the truss.
2. Stirrups transmit tension to these struts by means of bond, so that generally a biaxial state of strains prevails. The compression capacity of concrete is known to be drastically reduced when simultaneous transverse tensile strains are imposed.
3. The compression forces are introduced at the "joints" of the analogous truss, and these forces are far from being evenly distributed across the web. Eccentricities and transverse tensile stresses may be present.
4. Some diagonals may be inclined at an angle considerably smaller than 45 degree to the horizontal, and this will result in significant increase in diagonal compression stresses.

Sometimes a set of stirrups, crossed by a continuous diagonal crack, yields;

1. unrestricted widening of that crack then commences, and
2. one of the important components of shear resistance, aggregate interlock action, becomes ineffective.
3. The shear resistance so lost cannot be transferred to the dowel and the truss mechanisms, because they are already exhausted,
4. hence failure follows, with little further deformation.

To prevent such nonductile failure it is good practice indeed, in seismic design it is mandatory, to ensure that stirrups will not yield before the flexural capacity of the member is fully exhausted.



## 5 DESIGN FOR BOND

### 5.1 Introduction

For main longitudinal reinforcement in structural concrete members, deformed bars are normally used. This is because it is easier to ensure the development of bond and the anchorage of such main reinforcement compared with the case of plain bars. Even if the anchorage of the plain bars is secured by hooks or some other measures, still it is not so adequate to use plain bars for the main reinforcement of beams and columns. This is because, when plain bars are used instead of deformed bars, flexural cracks are more concentrated in a particular section of the member and such cracks opens wider. Hence the use of plain bars is not so convenient from the view point of the durability especially related to the corrosion of steel and may also lead to a significant reduction of member stiffness after cracking.

For the above reasons, in the ACI code (ACI318-08), it is specified that deformed bars shall be used for reinforcement, while plain bars are allowed for spirals or prestressing steel. In case of the New Zealand code (NZS3101:1995), plain bars are also permitted for stirrups and ties in addition to spirals and tendons. This is because the minimum diameters of bends required for plain bars are half of those required for deformed bars, and hence the stirrups and ties with plain bars can be bent with smaller diameter around the main reinforcement than those with deformed bars. Thus, for stirrups and ties, the use of plain bars may be more effective in order to constrain tightly the main longitudinal reinforcement than the use of deformed bars. Such effective constraint of longitudinal reinforcement is essential to prevent buckling of longitudinal reinforcement in an early stage of seismic loading more effectively.

In AIJ standard, plain bars used to be permitted even for main longitudinal reinforcement (see Art 14 for beams and Art 15 for columns in the AIJ Standard:1991). However, plain bars are seldom used for main longitudinal bars in recent years and round bars are not allowed for longitudinal reinforcement in 1999 AIJ standard. Also, in the AIJ structural design guidelines (1990), the use of deformed bars is specified for main longitudinal reinforcement.

### 5.2 Basic Theory for Bond

If we consider a simply supported beam subjected to a concentrated load as shown in Figure 5.1, the relation between  $M_1$  and  $M_2$  acting at the two cracked sections can be expressed as  $M_2 = M_1 + \Delta M$ . The moment,  $M$ , can be expressed as  $M = Tjd$ . By transforming this equation, the tension force in the reinforcement can be expressed by

$$T = \frac{M}{jd} \quad (5.1)$$

The increment of tension force in the reinforcement from section 1 to section 2,  $\Delta T$  can be expressed as

$$\Delta T = (\pi d_b) \mu \Delta x \quad (5.2)$$

where  $d_b$  is the bar diameter and  $\mu$  is the bond stress.




Figure 5.1 Average flexural bond stress (J.G. MacGregor, 'Reinforced Concrete', Prentice Hall, 1988)

If we assume the perfect beam action discussed in the section 2.2.3, the internal lever arm,  $jd$ , is constant. In this case, from Eq. (5.1), the increment of tension force  $\Delta T$  can be expressed as

$$\Delta T = \frac{\Delta M}{jd} \tag{5.3}$$

From Eqs. (5.2) and (5.3),

$$\frac{\Delta M}{\Delta X} = (\pi d_b) \mu jd \tag{5.4}$$

From the free body diagram in Figure 5.1(c),  $\Delta M = V \Delta X$ . Substituting this into Eq. (5.4),

$$V = (\pi d_b) \mu j d \quad (5.5)$$

By transforming Eq. (5.5),

$$\mu = \frac{V}{(\pi d_b) j d} \quad (5.6)$$

Eq. (5.6) corresponds to the following formula presented in the AIJ Standard,

$$\tau_a = \frac{Q}{\psi j} \leq f_a \quad (\text{AIJ-27})$$

Notation:

$Q$  = design shear force; design shear for the short-term loading shall conform to (3) of Item 2 in Art. 16 or (2) of Item 3 in Art. 16

$j$  = distance between tensile and compressive resultants of a flexural section and may be assumed to be  $(7/8)d$

$\psi$  = sum of perimeter of tensile reinforcing bars

$f_a$  = allowable bond stress (see Table 6, Art. 6).

## 6 SHEAR DESIGN OF RC MEMBERS BASED ON 'DESIGN GUIDELINES FOR EARTHQUAKE RESISTANT REINFORCED CONCRETE BUILDINGS BASED ON INELASTIC DISPLACEMENT CONCEPT' (1997)

### 6.1 Fundamental concept

#### 6.1.1 Plastic theory

##### 6.1.1.1 The lower bound theorem

If the load has such a magnitude that it is possible to find a stress distribution corresponding to stresses within the yield surface and satisfying the equilibrium condition and the statistical boundary conditions for the actual load, then this load will not be able to cause collapse of the body.

##### 6.1.1.2 The upper bound theorem

If various geometrically possible strain fields are considered, the work equation can be used to find values of the load carrying capacity that are greater than or equal to the true one.

##### 6.1.1.3 Scope

Philosophy of shear design in this guidelines is summarized as follows.

1. Ensure that the reliable shear strength is larger than design shear when the failure mechanism is reached.
2. The deformation capacity at the plastic hinge is considered in shear design.
3. Prevent a bond splitting failure.

##### 6.1.1.4 Shear resisting mechanisms

Arch action and truss action shown in Figure 6.1 are assumed to be the mechanisms resisting the shear force in this section. Use of the lower bound theory implies that **the equilibrium condition is satisfied** but **the compatibility of deformation in two actions is neglected**.




Figure 6.1 Idealized shear resisting mechanisms based on arch and truss actions

## 6.2 Design for shear of beams and columns

### 6.2.1 Code equations for shear strength of beams and columns

#### 6.2.1.1 Equations for shear strength

Shear strength can be expressed as the minimum of the following three equations. Same equations shall be used to members with axial force .

$$V_u = \mu \cdot p_{we} \cdot \sigma_{wy} \cdot b_e \cdot j_e + \left( \nu \cdot \sigma_B - \frac{5 \cdot p_{we} \cdot \sigma_{wy}}{\lambda} \right) \frac{b \cdot D}{2} \tan \theta \quad (6.1)$$

$$V_u = \frac{\lambda \cdot \nu \cdot \sigma_B + p_{we} \cdot \sigma_{wy}}{3} \cdot b_e \cdot j_e \quad (6.2)$$

$$V_u = \frac{\lambda \cdot \nu \cdot \sigma_B}{2} \cdot b_e \cdot j_e \quad (6.3)$$

where

$b$  is the width of the member as shown in Figure 6.2.

$D$  is the depth of the member as shown in Figure 6.2.

$b_e$  is the effective width for the truss actions.

$j_e$  is the effective depth and taken as the distance between the outermost stirrups.

$\sigma_{wy}$  is the reliable strength of web reinforcement.

$p_{we} = \frac{a_w}{b_e s}$  is the effective stirrup ratio where  $a_w$  is the section area of a set of stirrups,  $s$  is the spacing of stirrups.

$\mu = 2 - 20R_p$  is the coefficient to express the angle of compression strut of truss mechanism where  $R_p$  is the rotation angle at the plastic hinge.  $R_p$  can be assumed 0 when the plastic hinge is not expected.

$\nu$  is the effective compressive strength of concrete expressed as  $\nu = (1 - 20R_p) \cdot \nu_0$

$\nu_0$  is the effective compressive strength at non-hinge region expressed as

$$\nu_0 = 0.7 - \frac{\sigma_B}{200} \quad \text{where } \sigma_B \text{ is the compressive strength of concrete in N/mm}^2.$$

$\lambda$  is the effective depth coefficient for truss action expressed as

$$\lambda = 1 - \frac{s}{2j_e} - \frac{b_s}{4j_e}$$

$b_s$  is the maximum horizontal distance of web reinforcement as shown in Figure 6.2. If web reinforcement is placed evenly in the section,  $b_s$  can be

expressed as  $b_s = \frac{b_e}{N_s - 1}$  where  $N_s$  is the number of intermediate web

reinforcement.

$\theta$  is the angle of compression strut of arch mechanism.

$\tan \theta = 0$  when the member is subjected to tensile force.

$\tan \theta = 0.9 \times \frac{D}{2L}$  when  $\frac{L}{D} \geq 1.5$  and the member is subjected to compressive force or no axial force.

$\tan \theta = \frac{\sqrt{L^2 + D^2} - L}{D}$  when  $\frac{L}{D} < 1.5$  and the member is subjected to compressive force or no axial force.

where  $L$  is the clear length of member as shown in Figure 6.3.

If the member does not have a plastic hinge, the web reinforcement may be reduced to  $(1 - 10R_p)$  times the amount necessary for the plastic hinge region.




Figure 6.2 Definition of dimensions related to section geometry




Figure 6.3 Definition of column clear height

6.2.1.2 Amount of web reinforcement inside/outside the plastic hinge region

Amount of web reinforcement outside the plastic hinge region may be reduced by a factor of  $(1-10R_p)$ .

6.2.2 Explanations on shear strength without plastic hinge rotation

6.2.2.1 Shear capacity of truss action,  $V_t$ , and the angle of compressive strut,  $\phi$

Assuming the web reinforcement has yielded, the shear capacity from truss mechanism,  $V_t$ , is expressed as Eq. (6.4) by considering the Figure 6.4,

$$\begin{aligned} V_t &= \sum a_w \sigma_{wy} \\ &= p_{we} \sigma_{wy} b_e j_e \cot \phi \end{aligned} \quad (6.4)$$




Figure 6.4 Equilibrium of shear force in truss action

Angle  $\phi$  should take a certain range of value from the following three reasons.

(a) Effect of stress transfer across cracks

As  $\phi$  becomes smaller, or  $\cot \phi$  becomes greater, compressive stress transferred across cracks needs to become greater and the stress transfer becomes difficult. Upper limit of  $\cot \phi$  is set 2 in this guidelines, that is,

$$\cot \phi \leq 2 \quad (6.5)$$

(b) Effect of strain of longitudinal reinforcement

Note that the nominal yield strength of longitudinal reinforcement should be less than 390 MPa as the guidelines define. If the yield strength is larger than 390 MPa, the crack width tends to be larger and the compressive stress transfer across cracks becomes difficult. In this case, the upper limit of  $\cot \phi$  is suggested to be smaller than 2.0. However, this effect is not taken into account in this code.

(c) Effect of compressive stress of compression strut

From the equilibrium shown in Figure 6.5(b),

$$\left( \sum a_w \sigma_{wy} \right)^2 (1 + \cot^2 \phi) = (\sigma_t b_e \lambda j_e \cos \phi)^2 \quad (6.6)$$

Substituting Eq. (6.4) into Eq. (6.6),

$$(p_{we} \sigma_{wy} b_e j_e \cot \phi)^2 (1 + \cot^2 \phi) = (\sigma_t b_e \lambda j_e \cos \phi)^2 \quad (6.7)$$




Figure 6.5 Equilibrium at a nodal point in truss action

$$\begin{aligned} 1 + \cot^2 \phi &= \frac{(\sigma_t b_e \lambda j_e \cos \phi)^2}{(p_{we} \sigma_{wy} b_e j_e \cot \phi)^2} \\ &= \frac{(\sigma_t \lambda \cos \phi)^2}{(p_{we} \sigma_{wy} \cot \phi)^2} \\ &= \frac{(\sigma_t \lambda)^2}{(p_{we} \sigma_{wy})^2} \sin^2 \phi \\ &= \frac{(\sigma_t \lambda)^2}{(p_{we} \sigma_{wy})^2} \frac{1}{1 + \cot^2 \phi} \end{aligned} \quad (6.8)$$

Solving Eq. (6.8) for  $1 + \cot^2 \phi$ ,

$$1 + \cot^2 \phi = \frac{\sigma_t \lambda}{p_{we} \sigma_{wy}} \quad (6.9)$$

Solving Eq. (6.9) for  $\sigma_t$  and substituting it into  $\sigma_t \leq \nu_0 \sigma_B$

$$\sigma_t = (1 + \cot^2 \phi) \frac{p_{we} \sigma_{wy}}{\lambda} \leq \nu_0 \sigma_B \quad (6.10)$$

Then,

$$\cot \phi \leq \sqrt{\frac{\lambda \nu_0 \sigma_B}{p_{we} \sigma_{wy}} - 1} \quad (6.11)$$

Here the equations are summarized.



Substituting Eq. (6.5) into (6.4),

$$V_t = 2p_{we} \cdot \sigma_{wy} \cdot b_e \cdot j_e \quad (6.12)$$

Substituting Eq. (6.11) into (6.4),

$$V_t = p_{we} \cdot \sigma_{wy} \cdot b_e \cdot j_e \sqrt{\frac{\lambda v_0 \sigma_B}{p_{we} \sigma_{wy}} - 1} \quad (6.13)$$

Shear capacity can be expressed by the smaller of Eqs. (6.12) and (6.13). Two equations are expressed by Line OA and Line OABC in Figure 6.6(a). Line AB, or Eq. (6.13), can be approximated by the straight line as,

$$V_t = \frac{\lambda v_0 \sigma_B + p_{we} \cdot \sigma_{wy}}{3} \cdot b_e \cdot j_e \quad (6.14)$$

Line OABC has a negative slope after Point B since the web reinforcement was assumed to yield. However, if the amount of web reinforcement is greater than Point B, the compression strut reaches compressive strength before yielding of the web reinforcement. For this reason, the shear capacity after Point B is constant and expressed as,

$$V_t = \frac{\lambda v_0 \sigma_B}{2} \cdot b_e \cdot j_e \quad (6.15)$$

Equations for three shear capacities are shown in Figure 6.6(b).




Figure 6.6 Shear capacity due to truss action




Figure 6.7 Effective region in truss action

6.2.2.2 Shear capacity from arch action,  $V_a$

From Eq. (6.10), the compressive stress in the compressive strut in truss action is

$$\sigma_t = \frac{P_{we} \sigma_{wy}}{\lambda} (1 + \cot^2 \phi) \tag{6.16}$$

This can be expressed as Figure 6.8. When  $\cot \phi = 2$ , that is,  $\sigma_t \leq v_0 \sigma_B$ , the remaining axial compressive strength of the compressive strut,  $\sigma_a$ , can be expressed as

$$\sigma_a = v_0 \sigma_B - \frac{5 P_{we} \cdot \sigma_{wy}}{\lambda} \tag{6.17}$$




Figure 6.8 Compressive stress due to truss action




Figure 6.9 Shear capacity due to arch action

The realistic stress flow in Figure 6.9(a) is modeled as Figure 6.9(b) for simplicity and shear capacity based on the arch action is expressed as;

$$V_a = \sigma_a \frac{b \cdot D}{2} \tan \theta = \left( v_0 \sigma_B - \frac{5 p_{we} \cdot \sigma_{wy}}{\lambda} \right) \frac{b \cdot D}{2} \tan \theta \quad (6.18)$$

where  $\tan \theta = \frac{\sqrt{L^2 + D^2} - L}{D}$  from  $\tan \theta = \frac{D/2}{L + (D \tan \theta)/2}$  which is geometrically

derived from Figure 6.9(b). As shown in Figure 6.10,  $\tan \theta$  is asymptotically  $\frac{D}{2L}$

as  $\frac{L}{D}$  becomes greater and the equation for  $\tan \theta$  is conservative when  $\frac{L}{D} \leq 1.5$ .




Figure 6.10 Simplified equation for  $\tan \theta$

$$V_u = 2 \cdot p_{we} \cdot \sigma_{wy} \cdot b_e \cdot j_e + \left( v_0 \cdot \sigma_B - \frac{5 \cdot p_{we} \cdot \sigma_{wy}}{\lambda} \right) \frac{b \cdot D}{2} \tan \theta \quad (6.19)$$

$$V_u = \frac{\lambda \cdot v_0 \cdot \sigma_B + p_{we} \cdot \sigma_{wy}}{3} \cdot b_e \cdot j_e \quad (6.20)$$

$$V_u = \frac{\lambda \cdot v_0 \cdot \sigma_B}{2} \cdot b_e \cdot j_e \quad (6.21)$$

??? Why do we take a depth of arch as  $D/2$ ?

Assume that the depth of arch is  $x$ . Then the width of triangle under hydrostatic pressure,  $y$ , is  $x \tan \theta$ . To maximize  $V_a$ ,  $y = x \tan \theta$  needs to be maximized.




Figure 6.11 Depth of arch

Assume that the depth of arch is  $x$ . Then the width of triangle under hydrostatic pressure,  $y$ , is  $x \tan \theta$ . To maximize  $V_a$ ,  $y = x \tan \theta$  needs to be maximized.

From regular triangle,

$$\tan \theta = \frac{D-x}{L+x \tan \theta}, \text{ and hence } \tan \theta = \frac{-L \pm \sqrt{L^2 - 4x(x-D)}}{2x}. \quad (6.22)$$

Since  $y$  is positive, the following may be obtained.

$$y = \frac{-L + \sqrt{L^2 - 4x(x-D)}}{2}$$


Function  $y$  becomes maximum when  $L^2 - 4x(x-D)$  takes maximum, which happens at  $x = \frac{D}{2}$ . This can be understood by thinking the relation between the rectangle and triangle. By substituting  $x = \frac{D}{2}$  in (6.22), the angle of arch normally takes

$$\tan \theta = \frac{1}{2} \left( \sqrt{L^2 + D^2} - L \right)$$

This can be also understood from the geometry in Figure 6.11.

The relation between shear strength and the web reinforcement is shown in Figure 6.12.

Arch action diminishes when  $\frac{P_{we}\sigma_{wy}}{V\sigma_B} \geq \frac{\lambda}{5}$ .




(a) Shear capacity and amount of stirrups (b) Reduction of shear capacity due to plastic hinge rotation

**Figure 6.12 Design diagram for ductile member**

### 6.2.3 Truss mechanism at a transition region

Pending. 河野進書く。



(a) Truss action in a beam (b) Stress concentration near Point F

**Figure 6.13 Angle of compression struts in truss action**

### 6.2.4 Reduction of shear capacity due to plastic hinge rotation

Shear transfer becomes difficult at the plastic hinge region from the following two reasons.

- Reduction of effective compressive strength of concrete.  
Concrete compression strut needs to form in the cracked region as shown in Figure 6.14 and the compressive strength of concrete is considered less than that of cylinder test. Hence, the compressive strength is reduced by a factor,  $v_0$ , as shown in Figure 6.15(a) as a function of plastic hinge rotation,  $R_p$ . Although  $v_0$  may also be a function of crack width, this effect is neglected for simplicity.
- Change of angle of compressive strut of truss action.  
In non-plastic hinge region,  $\cot \phi$  is limited to be less than 2.0. However, widths of diagonal cracks become so large in the plastic hinge region that the compressive stress is difficult to transfer across cracks. Hence, the upper limit of  $\cot \phi$ ,  $\mu$ , is reduced as shown in Figure 6.15(b) as a function of plastic hinge rotation,  $R_p$ . If  $R_p = 0.05$  rad, angle of compression strut in truss action is fixed to 45 degrees.




Figure 6.14 Concrete compression strut




Figure 6.15 Assumption related to plastic deformation

### 6.2.5 Validation of the equations

Validation of the equations is shown in Figure 6.16. The ordinate is the ratio of experimental shear strength,  $V_{exp}$ , and the computed ultimate flexural strength,  $V_f$ , and the abscissa is the ratio of computed shear strength,  $V_{cal}$ , and  $V_f$ . Mean value and coefficient of variation of  $V_{exp}/V_f$  are 1.31 and 23.1% for 32 specimens with  $p_w=0$ , and 1.22 and 14.5% for 47 specimens with  $p_w>0$  and sufficient bond strength. These 47 specimens were reported to have failed in shear before flexural yielding.

Figure 6.17 shows the validation of equations in terms of six variables; concrete compressive strength, yield strength of web reinforcement, yield strength of longitudinal reinforcement, axial load level, web reinforcement ratio, shear span ratio.  $\nabla$  represents specimens with  $p_w=0$ .




Figure 6.16 Comparison between the computed shear capacity and experimental results






Figure 6.17 Accuracy of proposed equations for each variable

## 6.2.6 Design examples

### 6.2.6.1 Beam ( taken from Section 7.1.1 on p. 381 of Ref. 5 )

Compute the shear strength of the beam shown in Figure 6.18 with the following properties.

$$b \times D = 600\text{mm} \times 900\text{mm}$$

$$b_e = 600\text{mm} \text{ since the beam has slab on both sides.}$$

$$j_e = 740\text{mm}$$

Web reinforcement: 4 legs of D13 were set at 150 mm spacing for plastic hinge region, and 200 mm spacing for non-plastic hinge region

$$\sigma_B = 42\text{MPa}$$

$$R_p = 0.02 \text{ rad}$$

$$\sigma_{wy} = 800\text{MPa}$$

$V_L = 88\text{kN}$  is the design shear force under the dead load

$V_{mu} = 1060\text{kN}$  is the design shear force for the ultimate limit state

$$b_s = 200\text{mm}$$




Figure 6.18 Section configuration of a beam

$$\mu = 2 - 20R_p = 2 - 20 \times 0.02 = 1.60$$

$$v = (1 - 20R_p) \cdot v_0 = (1 - 20 \times 0.02) \times (0.7 - 42/200) = 0.6 \times 0.49 = 0.294$$

$$\text{Since } \frac{L}{D} = \frac{6000 - 950}{900} \geq 1.5,$$

$$\tan \theta = \frac{0.9D}{2L} = \frac{0.9 \times 900}{2 \times (6000 - 950)} = 0.802$$

$$\lambda = 1 - \frac{s}{2j_e} - \frac{b_s}{4j_e} = 1 - \frac{150}{2 \times 740} - \frac{200}{4 \times 740} = 0.831$$

Amount of web reinforcement outside the plastic hinge region may be increased by a factor of  $(1-10R_p)=0.80$ . Since spacing at the non-plastic region is 200mm, the effective web reinforcement ratio inside the plastic hinge region is recomputed based on spacing at  $200\text{mm} \times 0.80 = 160\text{mm}$

$$p_{we} = \frac{a_w}{b_e s} = \frac{508}{600 \times 160} = 0.00529$$

$$V_{u1} = \mu \cdot p_{we} \cdot \sigma_{wy} \cdot b_e \cdot j_e + \left( v \cdot \sigma_B - \frac{5 \cdot p_{we} \cdot \sigma_{wy}}{\lambda} \right) \frac{b \cdot D}{2} \tan \theta$$

$$= 1.60 \times 0.00529 \times 800 \times 600 \times 740 + \left( 0.294 \times 42 - \frac{5 \times 0.00529 \times 800}{0.831} \right) \times \frac{600 \times 900 \times 0.0802}{2}$$

$$= 3006\text{kN} + (12.4 - 25.5) \times \frac{600 \times 900 \times 0.0802}{2}$$

$$= 3006\text{kN} - 284\text{kN}$$

$$= 2722\text{kN}$$

The each term should be positive. Hence,  $V_{u1}$  is wrong.

$$V_{u2} = \frac{\lambda \cdot v \cdot \sigma_B + p_{we} \cdot \sigma_{wy}}{3} \cdot b_e \cdot j_e = \frac{0.831 \times 0.294 \times 42 + 0.00529 \times 800}{3} \times 600 \times 740$$

$$= 2145\text{kN}$$

$$V_{u3} = \frac{\lambda \cdot v \cdot \sigma_B}{2} \cdot b_e \cdot j_e = \frac{0.831 \times 0.294 \times 42 \times 600 \times 740}{2}$$

$$= 2278\text{kN}$$

$$V_u = \min(V_{u1}, V_{u2}, V_{u3}) = 2145\text{kN}$$

$$V = V_L + \phi V_{mu}$$

$$= 88\text{kN} + 1.30 \times 1060\text{kN} = 1466\text{kN} < V_u = 2145\text{kN}$$

OK!!!

Let us compute the shear strength with ACI code. Reduction factor for shear ( $\phi=0.85$ ) is not considered.

$$V_n = V_c + V_s = 544 + 2134 = 2678\text{kN}$$

$$V_c = \frac{b_w d \sqrt{f'_c}}{6} = \frac{600\text{mm} \cdot 840\text{mm} \cdot \sqrt{42\text{MPa}}}{6} = 544\text{kN}$$

$$V_s = \frac{A_v f_y d}{s} = \frac{508\text{mm}^2 \cdot 800\text{MPa} \cdot 840\text{mm}}{160\text{mm}} = 2134\text{kN}$$

**6.2.6.2** Column ( taken from Section 7.1.2 on p. 383 of Ref. 5 )

Compute the shear strength of column shown in Figure 6.19 with the following properties.

$$b \times D = 950 \times 950$$

$$b_e = 835 \text{ mm}$$


$$j_e = 835 \text{ mm}$$

Web reinforcement: 4 legs of D13 were set at 100 mm spacing for both plastic hinge region and non-plastic hinge region

$$\sigma_B = 42 \text{ MPa}$$

$$R_p = 0.01 \text{ radian}$$

$$\sigma_{wy} = 800 \text{ MPa}$$



**Figure 6.19** Section configuration of a column

$$\mu = 2 - 20R_p = 2 - 20 \times 0.01 = 1.80$$

$$\nu = (1 - 20R_p) \cdot \nu_0 = (1 - 20 \times 0.01) \times (0.7 - 42/200) = 0.8 \times 0.49 = 0.392$$

$$\lambda = 1 - \frac{s}{2j_e} - \frac{b_s}{4j_e} = 1 - \frac{100}{2 \times 835} - \frac{345}{4 \times 835} = 0.837$$

$$\tan \theta = \frac{0.9D}{2L} = \frac{0.9 \times 950}{2 \times 2600} = 0.164$$

$$\begin{aligned}
 V_{u1} &= \mu \cdot p_{we} \cdot \sigma_{wy} \cdot b_e \cdot j_e + \left( v \cdot \sigma_B - \frac{5 \cdot p_{we} \cdot \sigma_{wy}}{\lambda} \right) \frac{b \cdot D}{2} \tan \theta \\
 &= 1.80 \times 0.00608 \times 800 \times 835 \times 835 + \left( 0.392 \times 42 - \frac{5 \times 0.00608 \times 800}{0.837} \right) \times \frac{950 \times 950 \times 0.164}{2} \\
 &= 5172kN
 \end{aligned}$$

$$V_{u2} = \frac{\lambda \cdot v \cdot \sigma_B + p_{we} \cdot \sigma_{wy}}{3} \cdot b_e \cdot j_e = \frac{0.837 \times 0.392 \times 42 + 0.00608 \times 800}{3} \times 835 \times 835 = 4333kN$$

$$V_{u3} = \frac{\lambda \cdot v \cdot \sigma_B}{2} \cdot b_e \cdot j_e = \frac{0.837 \times 0.392 \times 42 \times 835 \times 835}{2} = 4804kN$$

$$V_u = \min(V_{u1}, V_{u2}, V_{u3}) = 4333kN$$

$$V = \sqrt{(\phi_X V_{mX})^2 + (\phi_Y V_{mY})^2} = \sqrt{(1.45 \times 1556)^2 + (1.41 \times 930)^2} = 2610kN < V_u \quad \text{OK!!!}$$

Let us compute the shear strength with ACI code.

$$V_n = V_c + V_s = 924 + 3658 = 4582kN$$

$$V_c = \frac{b_w d \sqrt{f'_c}}{6} = \frac{950mm \cdot 900mm \cdot \sqrt{42MPa}}{6} = 924kN$$

$$V_s = \frac{A_v f_y d}{s} = \frac{508mm^2 \cdot 800MPa \cdot 900mm}{100mm} = 3658kN$$

### 6.3 Design for bond

#### 6.3.1 Code equations

##### 6.3.1.1 Design bond stress

Consider design bond stress from the flexural action,  $\tau_f$ , in Figure 6.21. Assuming that the bond stress along a single reinforcing bar at the ultimate condition,  $\tau_f$ , is constant, the equilibrium for length  $(L-d)$  in the axial direction is expressed as follows.

$$\Delta\sigma \frac{\pi d_b^2}{4} = \tau_f (\pi d_b)(L-d) \quad (6.23)$$

Solve the equation for  $\tau_f$ .

$$\tau_f = \frac{d_b \cdot \Delta\sigma}{4(L-d)} \quad (6.24)$$

Here,  $\Delta\sigma$  may be computed using the following equation.

$$\begin{aligned} \Delta\sigma &= 2\sigma_{yu} && \text{(Both ends have plastic hinges)} \\ &= \sigma_{yu} + \sigma_y && \text{(One end has a plastic hinge)} \\ &= 2\sigma_y && \text{(No plastic hinge is planned)} \end{aligned} \quad (6.25)$$

Bond stress,  $\Delta\sigma$ , for reinforcement of the second layer may be computed using the following equation.

$$\begin{aligned} \Delta\sigma &= 1.5\sigma_{yu} && \text{(Both ends have plastic hinges)} \\ &= \sigma_{yu} + 0.5\sigma_y && \text{(One end has a plastic hinge)} \\ &= 1.5\sigma_y && \text{(No plastic hinge is planned)} \end{aligned} \quad (6.26)$$




Figure 6.20 Stresses acting on a reinforcing bar

### 6.3.1.2 Bond strength

Reliable bond strength,  $\tau_{bu}$ , is computed with the following equation.

$$\tau_{bu} = \alpha_t \left\{ (0.086b_i + 0.11) \sqrt{\sigma_B} + k_{st} \right\} \quad (\text{N/mm}^2) \quad (6.27)$$

where  $\alpha_t$  is the strength reduction factor for the top layer reinforcement and expressed as,

$$\alpha_t = \begin{cases} 0.75 + \sigma_B / 400 & \text{Reinforcement in the top layer of beams} \\ 1 & \text{Other reinforcement} \end{cases} \quad (\text{Unit: N/mm}^2) \quad (6.28)$$

and  $b_i$  is the length ratio of the bond splitting failure and expressed as,

$$\begin{aligned} b_i &= \min(b_{si}, b_{ci}) \\ b_{si} &= \frac{b - N_1 d_b}{N_1 d_b} \\ b_{ci} &= \frac{\sqrt{2}(d_{cs} + d_{ct}) - d_b}{d_b} \end{aligned} \quad (6.29)$$

Now,  $b$  is the section width,  $N_1$  the number of reinforcing bars in the first layer,  $d_{cs}$  the thickness of the side cover,  $d_{ct}$  the thickness of the top/bottom cover. The effect of web reinforcement,  $k_{st}$ , is expressed as follows.

$$k_{st} = \begin{cases} \left( 56 + \frac{47N_w}{N_1} \right) (b_{si} + 1) p_w & \text{for } b_{ci} \geq b_{si} \\ \frac{146A_w}{d_b s} & \text{for } b_{ci} < b_{si} \end{cases} \quad (\text{Unit: N/mm}^2) \quad (6.30)$$

where  $N_w$  is the number of legs of web reinforcement ( $= N_s + 2$ ),  $p_w$  web reinforcement ratio,  $A_w$  the section area of a single reinforcing bar,  $s$  the spacing of web reinforcing bar.

Reliable bond strength of the second layer web reinforcement,  $\tau_{bu2}$ , is expressed as,

$$\tau_{bu2} = \alpha_2 \alpha_t \left\{ (0.086b_{bi2} + 0.11) \sqrt{\sigma_B} + k_{st2} \right\} \quad (\text{N/mm}^2) \quad (6.31)$$

$$b_{si2} = \frac{b - N_2 d_b}{N_2 d_b} \quad (6.32)$$

where  $N_2$  is the number of reinforcing bars in the first layer.

$$k_{st2} = 103(b_{st2} + 1)p_w \quad (\text{N/mm}^2) \quad (6.33)$$

Index  $\alpha_2$  is supposed to be determined from the bond strength between the first and second layer reinforcement but may be determined from the following equation.

$$\alpha_2 = 0.6 \quad (6.34)$$

### 6.3.2 Effect of bond strength on Shear strength

Considering the bond strength, shear capacity,  $V_{bu}$ , is the minimum of Eq. (6.35) and Eq. (6.36).

$$V_{bu} = \sum(\tau_{bu}\phi)j_e + \left\{ v\sigma_B - \frac{2.5\sum(\tau_{bu}\phi)}{\lambda b_e} \right\} \frac{bD}{2} \tan \theta \quad (6.35)$$

$$V_{bu} = \frac{\lambda v\sigma_B}{2} b_e j_e \quad (6.36)$$

where

$$\sum(\tau_{bu}\phi) = \begin{cases} \tau_{bu} \sum \phi_1 + \tau_{bu2} \sum \phi_2 & \text{No plastic hinge possible} \\ (1-10R_p) \{ \tau_{bu} \sum \phi_1 + \tau_{bu2} \sum \phi_2 \} & \text{Plastic hinge possible} \end{cases} \quad (6.37)$$

$\sum \phi_1$  is the sum of peripheral length of the first layer web reinforcing bars,  $\sum \phi_2$  is that for the second layer.

### 6.3.3 Design examples

#### 6.3.3.1 Beam (taken from Section 7.2.1 on p. 385 of Ref. 5)

Compute the bond strength of the beam shown in Figure 6.21(a) with the following properties.

$$b \times D = 600\text{mm} \times 1000\text{mm}$$

Web reinforcement: 4 legs of D13 were set at 150 mm spacing for plastic hinge region, and 200 mm spacing for non-plastic hinge region

$$\sigma_B = 48\text{MPa}$$

$$\sigma_y = 400\text{MPa}$$

$$\sigma_{yu} = 1.25\sigma_y = 500\text{MPa}$$

$L = 5050\text{mm}$  is the clear span length

$d = 915\text{mm}$  is the effective depth






Figure 6.21 Section configurations of a beam

First, it was assumed that the beam have plastic hinges at both ends. The design bond stress for the first layer rebars,  $\tau_{f1}$ , is based on  $\Delta\sigma = 2\sigma_{yu} = 2 \times 500 \text{ MPa}$  (Eq. (6.25))

$$\tau_{f1} = \frac{d_b \cdot \Delta\sigma}{4(L-d)} = \frac{38 \times 2 \times 500}{4 \times (5050 - 915)} = 2.3 \text{ MPa}$$

From Eq. (6.28),

$$\alpha_t = 0.75 + \sigma_B / 400 = 0.75 + 48 / 400 = 0.87$$

From Eq. (6.29),

$$\begin{aligned} b_i &= \min(b_{si}, b_{ci}) = \min\left(\frac{b - N_1 d_b}{N_1 d_b}, \frac{\sqrt{2}(d_{cs} + d_{ct}) - d_b}{d_b}\right) \\ &= \min\left(\frac{600 - 4 \times 38}{4 \times 38}, \frac{\sqrt{2}(23.5 + 13 + 38/2 + 23.5 + 13 + 38/2) - 38}{38}\right) \\ &= \min(2.947, 3.13) = 2.947 \end{aligned}$$

From (6.30),

$$k_{st} = \left(56 + \frac{47N_w}{N_1}\right)(b_{si} + 1)p_w = \left(56 + 47 \times \frac{4}{4}\right)(2.947 + 1) \times 0.00423 = 1.72$$

The reliable bond strength,  $\tau_{bu1}$ , is from Eq. (6.27),

$$\begin{aligned} \tau_{bu} &= \alpha_t \left\{ (0.086b_i + 0.11)\sqrt{\sigma_B} + k_{st} \right\} = 0.87 \times \left\{ (0.086 \times 2.947 + 0.11)\sqrt{48} + 1.72 \right\} \\ &= 2.54 \text{ MPa} > \tau_{f1} \end{aligned}$$

Since it is assumed that the beam have plastic hinges at both ends, the design bond stress for the second layer rebars,  $\tau_{f2}$ , is based on  $\Delta\sigma = 1.5\sigma_{yu} = 1.5 \times 500 \text{ MPa}$  (Eq.(6.26)),

$$\tau_{f2} = \frac{d_b \cdot \Delta\sigma}{4(L-d)} = \frac{38 \times 1.5 \times 500}{4 \times (5050 - 915)} = 1.72 \text{MPa}$$

From (6.32),

$$b_{st2} = \frac{b - N_2 d_b}{N_2 d_b} = \frac{600 - 4 \times 38}{4 \times 38} = 2.947$$

From (6.33),

$$k_{st2} = 103(b_{st2} + 1) p_w = 103 \times (2.947 + 1) \times 0.00423 = 16.86$$

河野, SIでやり直し。

From (6.31),

$$\begin{aligned} \tau_{bu2} &= \alpha_2 \alpha_t \left\{ (0.0086 b_i + 0.11) \sqrt{\sigma_B} + k_{st2} \right\} \\ &= 0.6 \times 0.87 \times \left\{ (0.0086 \cdot 2.947 + 0.11) \sqrt{48} + 16.86 \right\} \\ &= 0.522 \times \{0.938 + 16.86\} \\ &= 2.17 \text{MPa} > \tau_{f2} \end{aligned}$$

### 6.3.3.2 Column ( taken from Section 7.2.2 on p. 387 of Ref. 5 )

Compute the bond strength of the column shown in Figure 6.22 with the following properties.

$$b \times D = 950 \text{mm} \times 950 \text{mm}$$

Web reinforcement: 4 legs of D13 were set at 80 mm spacing for both plastic hinge and non-plastic region.

$$\sigma_B = 48 \text{MPa}$$

$$\sigma_y = 400 \text{MPa}$$

$$\sigma_{yu} = 1.25 \sigma_y = 500 \text{MPa}$$

$L = 3000 \text{mm}$  is the clear span length

$d = 860 \text{mm}$  is the effective depth

First, it is assumed that the beam has a plastic hinge at one end and non-plastic hinge at the other end. The design bond stress for the first layer reinforcement,  $\tau_{f1}$ , is based on

$$\Delta\sigma = \sigma_{yu} + \sigma_y = (500 + 400) \text{MPa} \quad (\text{Eq. (6.25)})$$

$$\tau_{f1} = \frac{d_b \cdot \Delta\sigma}{4(L-d)} = \frac{38 \times (500 + 400)}{4 \times (3000 - 860)} = 4.0 \text{MPa}$$

Since reinforcement in the column is under consideration,  $\alpha_t$  is automatically 1 from Eq. (6.28).

$$\alpha_t = 1.0$$




Figure 6.22 Section configuration of a column

From Eq. (6.29)

$$\begin{aligned}
 b_i &= \min(b_{si}, b_{ci}) = \min\left(\frac{b - N_1 d_b}{N_1 d_b}, \frac{\sqrt{2}(d_{cs} + d_{ct}) - d_b}{d_b}\right) \\
 &= \min\left(\frac{950 - 5 \times 38}{5 \times 38}, \frac{\sqrt{2}(90 + 90) - 38}{38}\right) \\
 &= \min(4.0, 5.7) = 4.0
 \end{aligned}$$

From (6.30),

$$\begin{aligned}
 k_{st} &= \left(56 + \frac{47N_w}{N_1}\right)(b_{si} + 1)p_w \\
 &= \left(56 + 47 \times \frac{4}{5}\right)(4.0 + 1) \times 0.00668 \\
 &= 3.13
 \end{aligned}$$

The reliable bond strength,  $\tau_{bu1}$ , is from Eq.(6.27),

$$\begin{aligned}
 \tau_{bu1} &= \alpha_t \left\{ (0.086b_i + 0.11)\sqrt{\sigma_B} + k_{st} \right\} \\
 &= 1.0 \times \left\{ (0.086 \times 4.0 + 0.11)\sqrt{48} + 3.13 \right\} \\
 &= 6.27 \text{ MPa} > \tau_{f1}
 \end{aligned}$$

## 6.4 Design for shear of shearwalls

### 6.4.1 Shear cracking strength

Shear strength of shearwalls can basically be designed using the same except for beams and columns.

$$V_c = \frac{\tau_{scr} t_w l_w}{\chi_w} \quad (6.38)$$

$$\tau_{scr} = \frac{3(1+u)\{1-u^2(1-v)\}}{4\{1-u^3(1-v)\}} \quad (6.39)$$

$$u = \frac{l'_w}{l'_w + \sum D} \quad (6.40)$$

$$v = \frac{t_w}{b} \quad (6.41)$$

where  $t_w$  is the thickness of shearwall,  $l_w$  the center-center distance between boundary columns,  $l'_w$  the clear span between boundary columns,  $D$  the depth of boundary columns,  $b$  the width of boundary columns,  $\sigma_0$  the compressive stress of the shearwall due to vertical load,  $\sigma_T$  tensile strength of concrete and defined by the following equations.

$$\sigma_T = 0.313\sqrt{\sigma_B} \quad (\text{N/mm}^2) \quad (6.42)$$

河野進 図

### 6.4.2 Shear strength and $\nu$ for a hinge region

Shear strength of shearwalls can be expressed as

$$V_u = t_w l_w p_s \sigma_{sy} \cot \phi + \frac{1}{2} \tan \theta (1 - \beta) t_w l_{wa} \nu \sigma_B \quad (6.43)$$

where

$$p_s \sigma_{sy} = \frac{\nu \sigma_B}{2} \quad \text{when} \quad p_s \sigma_{sy} \geq \frac{\nu \sigma_B}{2} \quad (6.44)$$

$$\sigma_{sy} = 400 \text{MPa} \quad \text{when} \quad \sigma_{sy} \geq 400 \text{MPa} \quad (6.45)$$

$$\tan \theta = \sqrt{\left(\frac{h_w}{l_{wa}}\right)^2 + 1} - \frac{h_w}{l_{wa}}$$

$$(6.46)$$

$$\beta = \frac{(1 + \cot^2 \phi) p_s \sigma_{sy}}{v \sigma_B}$$

$$(6.47)$$

$$\cot \phi = 1.0$$

$$(6.48)$$

where  $\sigma_{sy}$  is the yield strength of web reinforcement and,  $t_w$  the thickness of shearwall,  $p_s$  the web reinforcement ratio of shearwall,  $h_w$  the height of shear wall and may be taken as the story height,  $\phi$  the angle of concrete compression strut, and  $l_{wa}$  and  $l_{wb}$  are the equivalent shearwall depths for truss and arch mechanisms, respectively.

The strength enhancement due to confining effect of boundary columns are taken into account in (6.43) by increasing the effective wall width. The effective width of the shearwall can be expressed as follows for truss and arch mechanisms, respectively.

$$l_{wa} = l'_w + D + \Delta l_{wa} \quad (6.49)$$

$$l_{wb} = l'_w + D + \Delta l_{wb} \quad (6.50)$$

where  $l'_w$  is the clear width of shearwall,  $D$  is the depth of boundary columns, and  $\Delta l_{wa}$  and  $\Delta l_{wb}$  are expressed as:

$$\Delta l_{wa} = \begin{cases} \frac{A_{ce}}{t_w} & \text{when } A_{ce} \leq t_w \cdot D \\ \frac{D + \sqrt{\frac{A_{ce} \cdot D}{t_w}}}{2} & \text{when } A_{ce} > t_w \cdot D \end{cases} \quad (6.51)$$

$$\Delta l_{wb} = \begin{cases} \frac{A_{ce}}{t_w} & \text{when } A_{ce} \leq t_w \cdot D \\ D & \text{when } A_{ce} > t_w \cdot D \end{cases} \quad (6.52)$$

where  $A_{ce}$  is the effective area of boundary columns.

$$A_{ce} = A_c - \frac{N_{cc}}{\sigma_B}$$

$$A_{ce} = 3t_w \cdot D \quad \text{when } A_{ce} \geq 3t_w \cdot D$$

$$(6.53)$$

where  $A_c$  is the area of compression column,  $N_{cc}$  is the axial force. When the effective width for the arch mechanism is computed using (6.49), the shear strength of side column should satisfy the following equation.

$$2 \cdot V_a \frac{\Delta l_{wa} - D/2}{l_{wa} \cdot \frac{(1 + \tan^2 \theta)}{2}} \leq V_{tc} \quad (6.54)$$

where  $V_a$  is the shear strength due to the arch mechanism,  $\tan \theta$  is the angle of arch mechanism,  $V_{tc}$  is the shear strength due to the truss mechanism of the boundary column. The effective width of the side column is:

$$b_e = \frac{A_{ce}}{D} - \beta \cdot t_w \quad (6.55)$$

where  $\beta$  is the contribution of truss mechanism to the shear strength of shearwall.

$$\nu = \nu_o \quad \text{for } R_u < 0.005 \quad (6.56)$$

$$\nu = (1.2 - 40R_u) \nu_o \quad \text{for } 0.005 < R_u < 0.02 \quad (6.57)$$

$$\nu = 0.4 \nu_o \quad \text{for } 0.02 < R_u \quad (6.58)$$

where  $R_u$  is the rotation angle of plastic hinge region.

### 6.4.3 Design examples

#### 6.4.3.1 Shearwall No. 1 ( taken from Section 7.4 on p. 391 of Ref. 5 )

Long term vertical load

$$N_L = 1070tf = 10486kN$$

Overturning moment

$$M_{wt} = 14430tf \cdot m = 141414kN \cdot m$$

Additional seismic vertical load coming from the frame transverse to the wall

$$N_L = 1070tf = 12564kN$$

$$R_u = 0.01$$

$$\cot \phi = 1.0$$

$$\sigma_B = 49.0 \text{ N/mm}^2$$

$$l'_w = 7050 \text{ mm}$$

Boundary columns

$$D_c = 950 \text{ mm}, \sigma_{wy} = 816 \text{ kN}, p_w = 0.00668, j_i = 770 \text{ mm}$$

Shearwall

$$t_w = 300 \text{ mm}, \sigma_{sy} = 306 \text{ N/mm}^2, p_s = 0.00663,$$

$$\text{Since } R_u = 0.01, v_0 = 0.7 - 49.0/200 = 0.455$$




Figure 6.23 Shearwall

$$A_{ce} = A_c - \frac{N_{cc}}{\sigma_B} = 950^2 - \frac{(10486 + 141414/8.0 + 12564 \cdot 1.3) \times 10^3}{49.0}$$

$$= -43400 \text{ mm}^2, \text{ hence } A_{ce} = 0 \text{ mm}^2$$

Since  $A_{ce} \leq t_w \cdot D = 300 \cdot 950 = 285000 \text{ mm}^2$ ,

$$\Delta l_{wa} = \frac{A_{ce}}{t_w} = \frac{0}{300} = 0.0 \text{ mm}$$

$$\Delta l_{wb} = \frac{A_{ce}}{t_w} = \frac{0}{300} = 0.0 \text{ mm}$$

Then,

$$l_{wa} = l'_w + D + \Delta l_{wa} = 7050 + 950 + 0.0 = 8000 \text{ mm}$$

$$l_{wb} = l'_w + D + \Delta l_{wb} = 7050 + 950 + 0.0 = 8000 \text{ mm}$$

$$\tan \theta = \sqrt{\left(\frac{h_w}{l_{wa}}\right)^2 + 1} - \frac{h_w}{l_{wa}} = \sqrt{\left(\frac{3600}{8000}\right)^2 + 1} - \frac{3600}{8000} = 0.647$$

$$\nu = (1.2 - 40R_u)\nu_o = (1.2 - 40 \cdot 0.01) \cdot 0.455 = 0.364$$

$$p_s \sigma_{sy} = 0.00663 \cdot 306 = 2.03 \text{ N/mm}^2 \quad \text{and} \quad \frac{\nu \sigma_B}{2} = 0.364 \cdot 49.0 / 2 = 8.91 \text{ N/mm}^2,$$

hence  $p_s \sigma_{sy} = 2.03 \text{ N/mm}^2$

$$\beta = \frac{(1 + \cot^2 \phi) p_s \sigma_{sy}}{\nu \sigma_B} = \frac{(1 + 1.0^2) \cdot 2.03}{0.364 \cdot 49.0} = 0.228$$

$$V_u = t_w l_w p_s \sigma_{sy} \cot \phi + \frac{1}{2} \tan \theta (1 - \beta) t_w l_{wa} \nu \sigma_B$$

$$= 300 \cdot 8000 \cdot 2.03 \cdot 1.0 + 0.5 \cdot 0.647 \cdot (1 - 0.228) \cdot 300 \cdot 8000 \cdot 0.364 \cdot 49$$

$$= 4871 + 10691 = 15562 \text{ kN}$$



## 7 AIJ STANDARD FOR STRUCTURAL CALCULATION OF REINFORCED CONCRETE STRUCTURES, REVISED IN 1991

### 7.1 Introduction

The articles which relate to shear and bond in the AIJ standard (1991) are listed in the following Sections 7.2 and 7.3. Most parts are extracted from the English version of the AIJ standard attached to the “AIJ Structural Design Guidelines for Reinforced Concrete Buildings (1994)”, but some modification of words and expressions were made for this lecture. Also, some private comments were attached.

### 7.2 Design for Shear

As mentioned in the introduction of this lecture note, in earthquake-resistant structures heavy emphasis is placed on ductility. When ductility is essential, the shear failure of structural members must be prevented in any case. In recent years, some theory-based shear design methods have been proposed, like the Nielsen truss analogy and the modified compression field theory by M. P. Collins. However, with respect to the shear problem, it seems too complicated to solve with a simple theory so far. Therefore, the semi-empirical equations proposed by Ohno and Arakawa, which are adopted in the following articles, are still being used.

#### 7.2.1 Art. 16 Shear Reinforcement in Beams and Columns

##### Item 1.

Design for shear in a rectangular or T-shaped beam or column shall satisfy the provisions in this article. Design for bond of longitudinal reinforcing bars shall satisfy the provisions of Item 1, Art.17. A member with other sectional shape shall be designed in conformance with the provisions above.

If the amount of shear reinforcement provided is confirmed to be sufficient by test or by other method, (1) and (2) in Item 2, and (3) in Item 3 need not be satisfied.

##### Item 2. Beams

(1) Allowable shear force  $Q_A$  of beams shall be calculated by the following formula:

$$Q_A = b j \left\{ \alpha f_s + 0.5 {}_w f_t (p_w - 0.002) \right\} \quad (\text{AIJ-22})$$

$$\text{where } \alpha = \frac{4}{\frac{M}{Qd} + 1} \text{ and } 1 \leq \alpha \leq 2$$

If value of  $p_w$  is greater than 1.2 percent, allowable shear force shall be calculated with  $p_w$  equal to 1.2 percent.

Notation:

b= width of beam or web width for a T-shaped beam

$j$  = distance between compressive and tensile resultants, and may be assumed to be  $(7/8)d$

$d$  = effective depth of beam

$p_w$  = transverse shear reinforcement ratio =  $a_w/(bx)$

$a_w$  = sectional area of a set of transverse shear reinforcement

$x$  = spacing of transverse shear reinforcement

$f_s$  = allowable shear stress of concrete

${}_w f_t$  = allowable tensile stress of transverse shear reinforcement

$\alpha$  = coefficient as a function of shear span ratio  $M/Qd$

$M$  = maximum design bending moment in the beam

$Q$  = maximum design shear force in the beam

(2) When bent-up bars are used with stirrups, equivalent reinforcement ratio,  $p_{we}$ , given by the following equation, may be used in Eq. (AIJ-22) instead of  $p_w$ , for a region over  $j/2$  on both sides from the ends of bent-up bars. The contribution of bent-up bars shall be ignored in a member subjected to load reversals.

$$p_{we} = \frac{a \sin \theta}{bj} \frac{f_t}{{}_w f_t} + p_w \quad (\text{AIJ-23})$$

for a set of bent-up bars.

Notation:

$a$  = sectional area of a set of bent-up bars

$\theta$  = angle of a bent-up bar with respect to the member axis (ordinarily, 45 degrees)

$f_t$  = allowable tensile stress of a bent-up bar for shear

(3) Design shear force  $Q_D$  under the short-term loading shall be calculated by Eq. (24). If design shear force under lateral loading, calculated in accordance with Item 1 in Art. 7, is multiplied by 1.5, Eq. (AIJ-24) need not be used.

$$Q_D = Q_L + \frac{\sum M_y}{\ell'} \quad (\text{AIJ-24})$$

Notation:

$Q_L$  = shear force under the long-term loading

$\sum M_y$  = sum of absolute yield moments at both beam ends

$\ell'$  = clear span length of beam.

(4) In addition to the provisions above, shear reinforcement shall be provided to satisfy the following requirements:

- 1) Size of stirrups shall be not less than  $\phi$  9 mm for plain bars and not less than D10 for deformed bars, except in the case of light shear reinforcement.
- 2) Spacing of stirrups shall not exceed  $(1/2)D$  nor 25 cm for  $\phi$  9 mm plain bars or D10 deformed bars, with or without bent-up bars. If larger size bars are used or more effective reinforcement is provided, the spacing may be increased within a limit of  $(1/2)D$  and 45 cm.
- 3) Shear reinforcement ratio shall be not less than 0.2 percent.
- 4) Stirrups shall enclose tension and compression reinforcing bars, and shall be arranged to confine the core concrete inside the longitudinal bars. The ends of stirrups shall be anchored by bending more than 135 degrees or the ends shall be welded together.
- 5) Angle of bent-up bars with the member axis shall be not less than 30 degrees.

### Item 3. Columns

(1) Allowable shear force  $Q_{AL}$  of columns for the long-term loading and allowable shear force  $Q_{AS}$  for the short-term loading shall be calculated by the following equations:

$$\begin{aligned} Q_{AL} &= b j \alpha f_s \\ Q_{AS} &= b j \left\{ f_s + 0.5 p_w f_t (p_w - 0.002) \right\} \end{aligned} \quad (\text{AIJ-25})$$

where,

$$\alpha = \frac{4}{\frac{M}{Qd} + 1} \quad \text{and} \quad 1 \leq \alpha \leq 2$$

If the value of  $p_w$  is greater than 1.2 percent, allowable shear force shall be calculated with  $p_w$  equal to 1.2 percent.

Notation:

b = width of column

j = distance between tensile and compressive resultants and may be assumed to be  $(7/8)d$

d = effective depth of column

$p_w$  = transverse shear reinforcement ratio =  $a_w/(bx)$

$a_w$  = sectional area of a set of transverse shear reinforcement

x = spacing of transverse shear reinforcement

$f_s$  = allowable shear stress of concrete

$f_t$  = allowable tensile stress of transverse shear reinforcement

$\alpha$  = coefficient as a function of shear span ratio  $M/Qd$  of column

$M$  = maximum design bending moment at column end

$Q$  = maximum design shear force in the column

(2) Design shear force for the short-term loading shall be a shear force at flexural yielding of the frame that includes the column under consideration. The value may be calculated using Eq. (AIJ-26) if an exact analysis is not performed. If design shear force under lateral loading, calculated in accordance with Item 1 in Art. 7, is multiplied by 1.5, Eq. (AIJ-26) need not be used.

$$Q_D = \frac{\sum M_y}{h'}$$

(AIJ-26)

Notation:

$M_y$  = sum of absolute yield moments at the top and bottom of a column. If one half of the sum of yield bending moments of beams connected to the column top is smaller than the yield moment of the column top, the smaller value may be used as the yield bending moment of that column top, except for the case of top story column. For the top of a top-story column, the sum of yield bending moments of beams, instead of half of it, must be compared with the yield moment of the column top.

$h'$  = clear height of column

(3) In addition to the above provisions, shear reinforcement shall satisfy the following requirements:

- 1) Size of a hoop shall be not less than  $\phi 9$  mm for plain bars and not less than D10 for deformed bars except for the case that spiral reinforcement is used or light shear reinforcement is sufficient.
- 2) Spacing of hoops shall not exceed 10 cm for  $\phi 9$  mm plain bars or D10 deformed bars. In a region more than 1.5 times maximum diameter of the column from the top and bottom, the spacing may be increased up to 1.5 times the above limit. If larger size bars are used or more effective reinforcement is provided, the spacing may be increased to 20 cm, appropriately.
- 3) Shear reinforcement ratio shall be not less than 0.2 percent.
- 4) Hoops shall enclose longitudinal bars, and shall be arranged to confine the core concrete inside the longitudinal bars. The ends of hoops shall be anchored by bending more than 135 degrees.
- 5) When shear force applied to a column likely reaches to a considerably large magnitude, the use of closed-shape hoops, which enclose the longitudinal bars and the ends of which are welded to each other, is desirable to ensure ductile behavior of the column.

---

--

## Comments

Figure 7.1 and Figure 7.2 show the background data which gave the basis of Eqs. (AIJ-22) and (AIJ-25). The technical term “shear intensity” used for the captions of these figures is defined in Section 4.2 in this lecture note. The plotted data in those figures were obtained from shear tests on about 1,200 beams conducted in Japan and overseas. **The size effects** of the tested beams were taken into account in the analyses of the test data as shown by the curves in Figure 7.3, in which the abscissa is for the effective depth of beams,  $d$  (cm) and the ordinate is for  $k_c$  (modification factor for cracking shear stress) and  $k_u$  (modification factor for shear stress at failure). The size effects were referred in Section 4.3.4.

When the tension reinforcement ratio,  $p_t = A_s / bd$ , is high in the shear span, the widths of flexural shear cracks are narrower at a given load, and this will enable aggregate interlock and dowel actions to carry larger load. The increased strength of the beam action due to larger flexural tension reinforcement has been demonstrated by some tests. This effect has been taken into account in Eq (11-5) in the ACI318-02 code. In the AIJ standard, this effect was neglected as can be seen from Eqs. (AIJ-22) and (AIJ-25), maybe assuming that such effect is negligible, compared with other factors, for a range of  $p_t$  from about 0.4 to 1 % which is normally used in practical design. When the test data were plotted in Figure 7.2, the effect of the tension reinforcement ratio was eliminated using the modification factor,  $k_p$ , shown in Figure 7.4.

The equivalent reinforcement ratio for a set of bent-up bars in Eq. (AIJ-23) was derived from the geometry of the bent-up bars with the assumed 45 degree cracks shown in Figure 7.5. In Figure 7.5, the spacing and the inclination of bent up bars are denoted by  $x'$  and  $\theta$ , respectively. Also, the tension stress on the potential cracked surface is denoted by  $\sigma$  in the figure. The derivation of Eq. (AIJ-23) can be seen in the commentary of the original AIJ standard (1991). A similar exercise has been conducted in Section 4.3.5 ( see **Figure 4.14**).

The notation of  $\Sigma M_y$  for Eq. (AIJ-26) is illustrated in Figure 7.6. It was assumed that the beams connected to the bottom end of the column will unlikely yield because the section size of those beams would be larger than that of the beams connected to the top end of the column. However, it is noted that, when a frame is designed so as to achieve the total yield mechanism (= beam side-sway mechanism) shown in Fig. C 3.2 in the AIJ Structural Design Guidelines, such assumption is not conservative.

---

--




図 15.1 普通コンクリート梁のせん断ひび割れ発生時応力度の実験値と計算値の比較

Figure 7.1 Relationship between Shear Stress Intensity at Shear Cracking and M/Qd




Figure 7.2 Relationship between Shear Stress Intensity at Shear Failure and M/Qd




Figure 7.3 Size Effects on Shear Strength




Figure 7.4 Effects of Tension Reinforcement Ratio on Shear Strength




Figure 7.5 Geometry to Determine Equivalent Reinforcement Ratio for Bent-up Bars,  $p_w$




Figure 7.6 Design Shear Force for Columns

### 7.3 Design for Development, Anchorage and Lap Splices

#### Art. 17 Bond, Anchorage and Lap Splices

##### Item 1. Bond

(1) Bond stress,  $\tau_a$ , along a tensile reinforcing bar in a flexural member due to shear shall be calculated by Eq. (AIJ-27), except when the provisions of Clause (2) are satisfied.

$$\tau_a = \frac{Q}{\psi j} \leq f_a$$

(AIJ-27)

Notation:

$Q$  = design shear force; design shear for the short-term loading shall conform to (3) of Item 2 in Art. 16 or (2) of Item 3 in Art. 16

$j$  = distance between tensile and compressive resultants of a flexural section and may be assumed to be  $(7/8)d$

$\psi$  = sum of perimeter of tensile reinforcing bars

$f_a$  = allowable bond stress (see Table 6, Art. 6).

(2) Distance,  $l_d$ , from critical section of tensile reinforcement in a flexural member to the end of the reinforcement in a span shall be calculated by Eq. (AIJ-28), except when the provisions in Clause (1) is satisfied (see Fig. 11).

$$l_d \geq \frac{\sigma_t a}{0.8 f_a \psi} + j$$

(AIJ-28)

Notation:

$l_d$  = distance from critical section to the end of a reinforcing bar

$\sigma_t$  = tensile stress of a reinforcing bar at the critical section, the value may be reduced to two thirds if the bar is hooked at the end

$a$  = sectional area of a reinforcing bar

$\psi$  = perimeter of a reinforcing bar

$f_a$  = allowable bond stress and values in Table 6, Art. 6

$j$  = distance between tensile and compressive resultants of a section in a flexural member, and may be assumed to be  $(7/8)d$



## Item 2. Anchorage and lap splices

(1) Development length of a longitudinal bar in a beam-column joint or length of a lap splice shall be calculated by Eq. (AIJ-29).

$$l_d \geq \frac{\sigma_t a}{f_a \psi}$$

(AIJ-29)

Notation:

$l_d$  = development length or length of a lap splice, excluding the length of a hook

$\sigma_t$  = maximum stress in an anchor part or at a lap splice, but value shall, in ordinary cases, be allowable stress for a lap splice. The value may be reduced to two-thirds if a bar is hooked at the end

$a$  = sectional area of a reinforcing bar

$f_a$  = allowable bond stress for top reinforcement, as specified in Table 6 in Art. 6 irrespective of position of the bar. The value may be increased by 1.5 times if the stress of reinforcement is compression, or if a deformed bar is anchored in a beam-column connection where bond split cracking is not anticipated, and

$\psi$  = perimeter of a reinforcing bar

(2) A lap splice shall, in general, be located at a region where both the member stress and reinforcement stress are small.

(3) Minimum anchor length and lap splice length shall be as specified in Table 10. The development length of bottom reinforcement in a floor slab and roof slab in a connection may be 15 cm for a plain bar with hook, and 10 d and 15 cm for a deformed bar for all steel grades and for all design standard strength and types of concrete. Anchor length of bottom reinforcement in a floor beam into a connection shall be 25d with hook for a plain bar, and 25d or 15d with hook for all steel grades and for all design standard strength and types of concrete.

(4) Plain bars of not less than 28 mm diameter and deformed bars not less than size D29 shall not be lap-spliced.

(5) A reinforcing bar shall be hooked at the ends. Deformed bars may not be hooked at the ends except in the following cases:

a) Corners of columns and beams, except in foundation beams

b) Chimneys.

Inside radius of a hook and of a bend shall conform to the provisions of "JASS 5."

(6) In a lap splice of welded wire mesh, the lap length between end transverse wires shall be not less than the sum of spacing of transverse wires and 5 cm nor less than 15 cm.

(7) In the anchorage region of welded wire mesh to the member fixed end, distance from the fixed face to the end transverse wire, shall be not less than the sum of spacing of transverse wires and 5 cm nor less than 15 cm.

### Comments

When the perfect beam action is achieved as assumed in Section 5.2, Eq. (AIJ-27) is adequate. This assumption will be acceptable for the service load condition which is normally not so severe. However, at an ultimate state under severe seismic loading, the diagonal tension cracks will open wide in the critical sections of members as shown in Figure 7.7(a). In this case, such assumption will not be legitimate any more. Equation (AIJ-28) seems to be more legitimate than Eq. (AIJ-27) for the purpose of securing the flexural strength of members.

When large diameter bars are placed over a length passing through interior beam-column joints of a frame, serious bond slip occurs and stiffness of the frame is significantly reduced under severe seismic actions as observed in many tests. Equation (AIJ-29) is not supposed to be applied to such a case as mentioned in the commentary of the AIJ Standard. In case of the New Zealand code, using formulae, the ratio of bar diameter to the column depth,  $b_d / h_c$ , is limited to about 1/20 to 1/35 to prevent such situation. Those formulae allow for the location of bars (top or bottom in the beam section) and also benefit of transverse pressure on the bars applied by column axial load. In case of the ACI code, it has been proposed to limit the ratio of  $b_d / h_c$  to be less than 20.




Figure 7.7 Effect of Diagonal Cracking on Development Length of Tension Reinforcement

## 8 SHEAR DESIGN OF RC MEMBERS BASED ON 'DESIGN GUIDELINES FOR EARTHQUAKE RESISTANT REINFORCED CONCRETE BUILDINGS BASED ON ULTIMATE STRENGTH CONCEPT' (1991)

### 8.1 Plastic theory

#### 8.1.1 The lower bound theorem

If the load has such a magnitude that it is possible to find a stress distribution corresponding to stresses within the yield surface and satisfying the equilibrium condition and the statistical boundary conditions for the actual load, then this load will not be able to cause collapse of the body.

#### 8.1.2 The upper bound theorem

If various geometrically possible strain fields are considered, the work equation can be used to find values of the load carrying capacity that are greater than or equal to the true one.

### 8.2 Scope

1. Ensure that the reliable shear strength is large than design shear when the failure mechanism is reached
2. Ensure that the deformation capacity at the plastic hinge.
3. Prevent a bond splitting failure.

### 8.3 Shear strength of beams and columns

Shear strength can be expressed with the following equation. Use

$$p_w \cdot \sigma_{wy} = \frac{v \cdot \sigma_B}{2} \quad \text{when} \quad p_w \cdot \sigma_{wy} \geq \frac{v \cdot \sigma_B}{2}.$$

$$V_u = b \cdot j_t \cdot p_w \cdot \sigma_{wy} \cdot \cot \phi + \frac{\tan \theta \cdot (1 - \beta) \cdot b \cdot D \cdot v \cdot \sigma_B}{2} \quad (8.1)$$

Truss  
action

Arch  
action

where

$$\tan \theta = \sqrt{\left(\frac{L}{D}\right)^2 + 1} - \frac{L}{D} \quad (8.2)$$

and


$$\beta = \frac{(1 + \cot^2 \phi) \cdot p_w \cdot \sigma_{wy}}{v \cdot \sigma_B}. \quad (8.3)$$

Based on the lower bound theorem in Limit analysis by Nielsen


Equilibrium	with respect to the shear force
Plastic criteria	shear rebar reached yielding
	Concrete strut reached its effective strength $v\sigma_B$

Longitudinal rebar is assumed infinitely strong.

8.3.1 The first term (contribution from the truss action)



a) Analogous truss model



b) Equilibrium of an infinitesimal stringer element

Figure 8.1 Truss mechanism

The equilibrium of the free body in the vertical direction is,

$$V_t = (c \sigma_t \cdot b \cdot j_t \cdot \cos \phi) \sin \phi \quad (8.4)$$

Since the vertical components of forces in diagonal strut and the stirrup need to be same.

$$c \sigma_t \cdot b \cdot j_t \cdot x \cdot \sin \phi \cdot \sin \phi = b \cdot x \cdot p_w \cdot \sigma_{wy} \quad (8.5)$$

$$c \sigma_t = \frac{p_w \cdot \sigma_{wy}}{\sin^2 \phi} = (1 + \cot^2 \phi) \cdot p_w \cdot \sigma_{wy} \quad (8.6)$$

Hence we have

$$\begin{aligned} V_t &= \frac{p_w \cdot \sigma_{wy}}{\sin^2 \phi} \cdot b \cdot j_t \cdot \cos \phi \cdot \sin \phi \\ &= p_w \cdot \sigma_{wy} \cdot b \cdot j_t \cdot \cot \phi \end{aligned}$$

(8.7)

8.3.2 The second term (contribution from the arch action)




Figure 8.2 Arch mechanism

After truss mechanism takes up  $c\sigma_t$  out of  $v \cdot \sigma_B$  which is the compressive capacity of concrete strut,  $v \cdot \sigma_B - c\sigma_t$  can be used for the arch action. Neglecting the angle of truss and arch,

$$\begin{aligned}
 V_a &= c\sigma_a \cdot b \cdot \frac{D}{2} \cdot \tan \theta \\
 &= c\sigma_a \cdot b \cdot \frac{D}{2} \cdot \left\{ \sqrt{\left(\frac{L}{D}\right)^2 + 1} - \frac{L}{D} \right\} \\
 &= (v\sigma_B - c\sigma_t) \cdot b \cdot \frac{D}{2} \cdot \tan \theta
 \end{aligned}
 \tag{8.8}$$

8.3.3 Integration of the truss and arch actions

$$\begin{aligned}
 V_u &= V_t + V_a \\
 &= b \cdot j_t \cdot p_w \cdot \sigma_{wy} \cdot \cot \phi + (v\sigma_B - c\sigma_t) \cdot b \cdot \frac{D}{2} \cdot \tan \theta \\
 &= b \cdot j_t \cdot p_w \cdot \sigma_{wy} \cdot \cot \phi + v\sigma_B \left(1 - \frac{c\sigma_t}{v\sigma_B}\right) \cdot b \cdot \frac{D}{2} \cdot \tan \theta \\
 &= b \cdot j_t \cdot p_w \cdot \sigma_{wy} \cdot \cot \phi + v\sigma_B (1 - \beta) \cdot b \cdot \frac{D}{2} \cdot \tan \theta
 \end{aligned}
 \tag{8.9}$$

Truss  
action

Arch  
action



### 8.3.5 Coefficients for members with plastic hinges

Assume that  $R_p$  denotes the rotational angle at the yield hinge, then the effectiveness factor  $\nu$  can be expressed by the following two equations or Figure 8.4.

$$\nu = (1.0 - 15R_p)\nu_o \quad \text{for } 0 < R_p < 0.05 \quad (8.14)$$

$$\nu = 0.25 \cdot \nu_o \quad \text{for } R_p > 0.05 \quad (8.15)$$




Figure 8.4 Relationship between the guaranteed hinge rotation  $R_p$  and  $\nu$

The value of  $\cot \phi$  is the minimum of the following four equations. The first two equations are shown in Figure 8.5.

$$\cot \phi = 2.0 - 50R_p \quad \text{for } 0 < R_p < 0.02 \quad (8.16)$$

$$\cot \phi = 1.0 \quad \text{for } 0.02 < R_p \quad (8.17)$$

$$\cot \phi = \frac{j_t}{D \cdot \tan \theta} \quad (\text{SAME as EQ. (8.11)}) \quad (8.18)$$

$$\cot \phi = \sqrt{\frac{\nu \sigma_B}{P_w \cdot \sigma_{wy}} - 1} \quad (\text{SAME as EQ. (8.12)}) \quad (8.19)$$




Figure 8.5 Relationship between the guaranteed hinge rotation  $R_p$  and  $\cot \phi$

**8.3.6 Minimum reinforcement**  
0.2% for all beams and columns

**8.4 Shear strength of walls**

**8.4.1 Shear strength**

Basically the same except

1.  $f_y$  should be smaller than 400 MPa.
2.  $\cot \phi = 1.0$
3.  $\nu$  and  $\nu_o$  have been set especially for the wall
4. Column size is taken into account for arch action.
5. Shear is checked for each story and hence the method assuring the shear transfer between stories is provided.

**8.4.2 Equivalent wall widths**

Equivalent wall widths are different for truss action and arch action.

**8.4.3 Effective factor of concrete for a non-hinge region**

Eq. (8.13) in Section 8.3.4 can be used.


**8.4.4 Effective factor of concrete for a hinge region**

$$\nu = \nu_o \text{ for } R_p < 0.005$$

$$\nu = (1.2 - 40R_p)\nu_o \text{ for } 0.005 < R_p < 0.02 \tag{8.20}$$

$$\nu = 0.4 \cdot \nu_o \text{ for } 0.02 < R_p \tag{8.21}$$

$$\nu = 0.4 \cdot \nu_o \text{ for } 0.02 < R_p \tag{8.22}$$



**Figure 8.6 Effectiveness factor of concrete,  $\nu_m$ , and deformation capacity**



#### 8.4.5 Beam between stories

A fraction of shear carried by the arch mechanism of the upper story is directly transferred to the arch mechanism of the lower story. The rest of the shear carried by the arch mechanism of the upper story needs to be transferred to the lower story through the tensile action of beams or the truss mechanism in the lower story.

#### 8.4.6 Minimum reinforcement

0.25% for walls.

0.3% for plastic hinge region of the boundary columns.

### 8.5 Bond

#### 8.5.1 Design bond stress

$\tau_f$  from a flexural action

$$\Delta\sigma \frac{\pi d_b^2}{4} = \tau_f (\pi d_b)(L-d) \quad (8.23)$$

$$\tau_f = \frac{d_b \cdot \Delta\sigma}{4(L-d)} \quad (8.24)$$

$$\begin{aligned} \Delta\sigma &= 2\sigma_{yu} \\ &= \sigma_{yu} + \sigma_y \\ &= 2\sigma_y \end{aligned} \quad (8.25)$$

$\tau_t$  from a truss mechanism

$$\Delta T = \tau_t \sum \psi \cdot \Delta x \quad (8.26)$$

$$\Delta T = \frac{\Delta M}{j_t} = \frac{V_t}{j_t} \cdot \Delta x \quad (\text{Perfect beam action was assumed.}) \quad (8.27)$$

$$\tau_t = \frac{V_t}{\sum \psi \cdot j_t} = \frac{b \cdot j_t \cdot p_w \cdot \sigma_{wy} \cdot \cot \phi}{\sum \psi \cdot j_t} = \frac{b \cdot p_w \cdot \sigma_{wy} \cdot \cot \phi}{\sum \psi} \quad (8.28)$$

#### 8.5.2 Bond strength

$$\tau_{bu} = \left( 1.2 + 5 \frac{p_w}{d_b} \right) \sqrt{\sigma_B} \quad (8.29)$$

Bond strength for the top reinforcement of a beam shall be reduced to 0.8 times the value in Eq. (8.29)).

## REFERENCES

1. Park, R. and Paulay Thomas, Reinforced Concrete Structures, John Wiley & Sons, 1975.
2. James G. MacGregor, Reinforced Concrete Mechanics and Design, Prentice Hall, 1988.
3. AIJ structural design guidelines for reinforced concrete buildings based on ultimate strength concept (Japanese), Architecture Institute of Japan, 1990.
4. AIJ structural design guidelines for reinforced concrete buildings based on ultimate strength concept (English), Architecture Institute of Japan, 1994.
5. AIJ structural design guidelines for reinforced concrete buildings based on inelastic displacement concept (Japanese), Architecture Institute of Japan, 1997.
6. 渡邊史夫, 窪田敏行 : エース建築工学シリーズ エース 鉄筋コンクリート構造, 朝倉書店, 2003年.
7. 林静雄, 北山和宏, 衣笠秀行, 坂田弘安 : 建築家のための鉄筋コンクリート構造, 市ヶ谷出版社, 2007年.

## ACKNOWLEDGEMENT

The class note on shear and bond was originally compiled by Professor Emeritus Hitoshi Tanaka of the Disaster Prevention Research Institute, Kyoto University, as a lecture note for the International Institute of Seismology and Earthquake Engineering, Building Research Institute. The content was modified and a chapter on flexure was added later. Design equations of shear strength was also added from the AIJ structural design guidelines for reinforced concrete buildings based on inelastic displacement concept.

## HOW TO REACH ME

### Susumu KONO

Professor

Institute of Innovative Research

Tokyo Institute of Technology

Nagatsuta 4259, G5-1

Midori, Yokohama, 226-8503, Japan

Tel/Fax: +81-45-924-5384

Email: kono.s.ae@m.titech.ac.jp

WWW: <http://www.msl.titech.ac.jp/~serc/kono/>